

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C02F 1/56, C08F 220/34		A1	(11) International Publication Number: WO 98/14405																																				
			(43) International Publication Date: 9 April 1998 (09.04.98)																																				
(21) International Application Number: PCT/US97/16647			(72) Inventors: HUANG, Sun-Yi; 106 New England Drive, Stamford, CT 06903 (US). ROSATI, Louis; 30 West Road, South Salem, NY 10590 (US). KOZAKIEWICZ, Joseph, J.; 54 Barnswallow Drive, Trumbull, CT 06611 (US). COVILLE, Michael, W.; 175 Saw Mill Road, Stamford, CT 06903 (US).																																				
(22) International Filing Date: 16 September 1997 (16.09.97)																																							
(30) Priority Data:																																							
<table><tr><td>08/720,851</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/725,325</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/720,840</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/725,521</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/726,845</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/724,988</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/724,970</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/725,586</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/727,693</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/723,656</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/725,522</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr><tr><td>08/725,865</td><td>3 October 1996 (03.10.96)</td><td>US</td></tr></table>				08/720,851	3 October 1996 (03.10.96)	US	08/725,325	3 October 1996 (03.10.96)	US	08/720,840	3 October 1996 (03.10.96)	US	08/725,521	3 October 1996 (03.10.96)	US	08/726,845	3 October 1996 (03.10.96)	US	08/724,988	3 October 1996 (03.10.96)	US	08/724,970	3 October 1996 (03.10.96)	US	08/725,586	3 October 1996 (03.10.96)	US	08/727,693	3 October 1996 (03.10.96)	US	08/723,656	3 October 1996 (03.10.96)	US	08/725,522	3 October 1996 (03.10.96)	US	08/725,865	3 October 1996 (03.10.96)	US
08/720,851	3 October 1996 (03.10.96)	US																																					
08/725,325	3 October 1996 (03.10.96)	US																																					
08/720,840	3 October 1996 (03.10.96)	US																																					
08/725,521	3 October 1996 (03.10.96)	US																																					
08/726,845	3 October 1996 (03.10.96)	US																																					
08/724,988	3 October 1996 (03.10.96)	US																																					
08/724,970	3 October 1996 (03.10.96)	US																																					
08/725,586	3 October 1996 (03.10.96)	US																																					
08/727,693	3 October 1996 (03.10.96)	US																																					
08/723,656	3 October 1996 (03.10.96)	US																																					
08/725,522	3 October 1996 (03.10.96)	US																																					
08/725,865	3 October 1996 (03.10.96)	US																																					
(71) Applicant: CYTEC TECHNOLOGY CORP. [US/US]; Suite 1052, 1105 North Market Street, Wilmington, DE 19801 (US).																																							
			(74) Agents: SCHULTZ, Claire, M. et al.; Cytec Industries Inc., 1937 West Main Street, P.O. Box 60, Stamford, CT 06904-0060 (US).																																				
			(81) Designated States: AL, AM, AU, AZ, BA, BB, BG, BR, BY, CA, CN, CU, CZ, EE, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, RO, RU, SD, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).																																				
			Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>																																				
(54) Title: AQUEOUS DISPERSIONS																																							
(57) Abstract <p>Aqueous dispersion of polymers is provided which comprises: (a) a first cationic water-soluble or water-swellaable polymer; and (b) at least one second water-soluble polymer different from said first polymer; and (c) a kosmotropic salt; and (d) a chaotropic salt, wherein the amounts of said (b), and (d) are such that a homogeneous composition is obtained in the absence of said (b). Process to form an aqueous dispersion. Method for dewatering a suspension of dispersed solids and method to produce clarified water using said dispersion.</p>																																							

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Aqueous Dispersions

Background of the Invention

5 This invention relates to aqueous dispersions comprised of water-soluble polymers, processes for making said dispersions, and methods of using said dispersions in water treating, dewatering, water clarification, papermaking, oil field, soil conditioning, food processing, mineral processing, and biotechnological applications.

10 U.S. Patent No. 4,380,600 discloses a process for producing an aqueous dispersion of water-soluble polymers. The aqueous dispersion may contain inorganic salt. However, the aqueous dispersions exemplified therein have disadvantageously high bulk viscosities.

15 U.S. Patent No. 4,673,704 and EP 0 170 394 A2 disclose products comprised of particles above 20 microns in size of a high molecular weight polymer gel interconnected by a continuous phase that is an aqueous solution of an equilibrating agent that holds the water content of the particles in equilibrium with the water content of the aqueous phase and that prevents substantial agglomeration of the particles in the fluid product. Although these references are entitled "Aqueous Polymer Dispersions," the products disclosed therein are distinguished from the aqueous dispersions of U.S. Patent No. 4,380,600 and from the aqueous dispersions of the instant invention in that the particles of U.S. 4,673,704 and EP
20 0 170 394 A2 are not generally held suspended in a continuous matrix of the aqueous phase but instead generally rest substantially in contact with one another but slide over one another. A process for dispersing the polymer gel into an aqueous solution of an equilibrating agent and working the polymer while in that medium is disclosed in U.S. Patent No. 4,778,836 and EP 0 169 674 B1. Also, U.S. Patent No. 4,522,968 discloses a process
25 for dispersing certain powdered water-soluble homopolymers or copolymers in an aqueous solution containing a polymer of ethylene oxide and/or propylene oxide.

30 U.S. Patent Nos. 4,929,655 and 5,006,590 disclose processes for preparing aqueous dispersions of water-soluble polymers by polymerizing benzyl-containing monomers in the presence of an organic high molecular multivalent cation and a multivalent anionic salt. The benzyl group-containing monomer may be replaced by a hydrophobic alkyl group-containing monomer as in EP 0 525 751. Numerous references concern these and similar polymers, e.g. U.S. 5,332,506; 5,332,507; 5,330,650; 5,292,793; 5,435,922; 5,466,338; EP 0 595 156 A1; EP 0 630 909 A1; EP 0 657 478 A2; EP 0 629 583 A2; EP 0 617 991 A1, EP 0 183 466 B1, EP 0 637 598 A2; EP 0 717 056 A2; JP 61-6396; JP 61-6397; JP 61-6398; JP 62-262799; JP 64-15130; JP 2-38131; JP 62 15251; JP 61-138607; Hei 6-329866; and JP 62-
35

100548. Although some of the aqueous dispersions in these references have relatively low bulk viscosities, the need to include special monomers containing aromatic or hydrophobic alkyl groups in order to render the polymer insoluble in salt solution may be disadvantageous because the special monomers may be expensive and dilutive of the polymer effect in a specific application.

The effect of salts on the solubility of various substances in aqueous solution is well discussed in the scientific literature. The "Hofmeister" series ranks anions according to their ability to increase or decrease the solubility of substances in water. Although positions in the ranking may vary slightly, depending on the substance, a generally accepted ranking of the anions is:

Salting-out (kosmotropic)	$\text{SO}_4^{2-} \sim \text{HPO}_4^{2-} > \text{F}^- > \text{Cl}^- > \text{Br}^- > \text{I}^- \sim \text{ClO}_4^- > \text{SCN}^-$	Salting-in (chaotropic)
------------------------------	--	----------------------------

Kosmotropic salts generally decrease the solubility of substances in water. For instance, the Hofmeister ranking apparently guided the choice of salts for precipitating cationic water soluble polymers, containing hydrophobic groups, in U. S. Patent Nos. 4, 929,655 and 5,006,590, as well as EP 0 630 909 A1, EP 0 525 751 A1, and EP 0 657 478 A2, as evidenced by their use of strongly kosmotropic salts containing sulfate and phosphate anions. On the other hand, chaotropic salts generally increase the solubility of substances in water.

There are numerous means known to those skilled in the art for determining whether a particular salt is kosmotropic or chaotropic. Representative salts which contain anions such as sulfate, fluoride, phosphate, acetate, citrate, tartrate and hydrogenphosphate are kosmotropic. Representative salts which contain anions such as thiocyanate, perchlorate, chlorate, bromate, iodide, nitrate and bromide are chaotropic. The chloride anion is generally considered to be at about the middle of the Hofmeister ranking, being either weakly chaotropic or weakly kosmotropic, depending on the particular system. In the instant invention, although occasionally chaotropic, inorganic salts which contain the chloride anion tend to be kosmotropic.

Small amounts of sodium thiocyanate, for instance about 0.1% by weight, on total, have been reported to be useful as stabilizers for polymer dispersions as in EP 0 657 478 A2, where $(\text{NH}_4)_2\text{SO}_4$ was used to deposit the polymer. Sodium thiocyanate and sodium iodide have been reported to be useful as stabilizers for hydroxylamine-containing water-soluble polymer systems, as in EP 0 514 649 A1. U.S. 3,234,163 teaches that small amounts of thiocyanate salts,

preferably 0.1 to 1 percent, based on the weight of the polymer, are useful for stabilizing polyacrylamide solutions.

5 The Hofmeister ranking has been observed in solutions of high molecular weight, water-soluble polymers. For instance, the effect of various salts on the solubility of synthetic, water-soluble polymers was explored by Shuji Saito, J. Polym. Sci.: Pt. A, Vol. 7, pp. 1789-1802 (1969). This author discussed the effect of various anions on polymer solubility and stated "This anionic order seems to be independent of the type of counter cations and is in line with Hofmeister's lyotropic series for anions." Similarly, in M. Leca, Polymer Bulletin, Vol. 16, pp. 537-543, 1986, the viscosity of polyacrylamide, as determined in 1N solutions of various salts, 10 was found to increase in the order $\text{HPO}_4^{2-} < \text{H}_2\text{O} < \text{Br}^- < \text{NO}_3^- < \text{I}^- = \text{BrO}_3^- < \text{ClO}_3^- = \text{SCN}^-$. The viscosities were reported to be higher in more chaotropic salt solutions than in less chaotropic, or kosmotropic, salt solutions. Certain novel cationic polyelectrolytes, termed ionene polymers, were reported (D. Casson and A. Rembaum, Macromolecules, Vol. 5, No. 1, 1972, pp. 75-81) to be insoluble in either 0.4 M potassium iodide or 0.4 M potassium thiocyanate. It has also 15 been reported (W-F. Lee and C-C. Tsai, J. Appl. Polym. Sci., Vol. 52, pp. 1447-1458, 1994) that poly(trimethyl acrylamido propyl ammonium iodide) did not dissolve in 0.5 M Na_2ClO_4 or 0.5 M NaNO_3 .

Certain anionic organic salts, such as hydrotropes and surfactants, also tend to increase the solubility of substances in water. However, poly(allylammonium chloride) was reported (T. 20 Itaya et al., J. Polym. Sci., Pt. B: Polym. Phys., Vol. 32, pp. 171-177, 1994, and references 3, 5 and 6 therein; also Macromolecules, Vol 26, pp. 6021-6026, 1993) to precipitate in solutions containing the sodium salt of p-ethylbenzenesulfonate, p-propylbenzenesulfonate or naphthalenesulfonate. Poly(4-vinyl pyridine) quaternized with butyl chloride and poly(allylammonium chloride) were reported (M. Satoh, E. Yoda, and J. Komiyama, 25 Macromolecules, Vol. 24, pp. 1123-27, 1991) to precipitate in solutions of NaI and also in solutions containing the sodium salt of p-ethylbenzenesulfonate, respectively. Compositions comprising sulphonated hydrocarbon surfactants and hydrophilic cationic polymers were disclosed in U.S. Patent No. 5,130,358. Mixtures of chaotropic salts, or anionic organic salts, and kosmotropic salts may be used to precipitate cationic polymers as in U.S. Application Serial 30 No. (attorney docket No. 96052), filed even date herewith.

Aqueous dispersions of water-soluble polymers are disclosed in U.S. 5,403,883; 5,480,934; 5,541,252; EP 0 624 617 A1; EP 0 573 793 A1; and WO 95/11269. A problem remains in that the aqueous dispersions exemplified in these references still have relatively high bulk viscosities.

A process for preparing crosslinked copolymer beads from water-soluble monomers in an aqueous solution containing an inorganic salt and a dispersant is disclosed in U.S. 5,498,678 and EP 0 604 109 A2. Mixtures of aqueous dispersions and water-in-oil emulsions are disclosed in Hei 7-62254 and Hei 6-25540. The addition of a nonionic surfactant and an oleaginous liquid to an aqueous dispersion to maintain flowability is disclosed in U.S. Patent No. 5,045,587. Mixtures of cationic polymers are disclosed in Sho-52-71392 and homogeneous blends of water-soluble polymers are disclosed in U.S. Patent No. 4,835,206 and EP 0 262 945 B1. Bimodal cationics for water clarification are disclosed in U.S. Patent Nos. 4,588,508 and 4,699,951. Blends of water-in-oil polymer emulsions are disclosed in U.S. Patent Application Serial No. 08/408,743.


In spite of the effort to make satisfactory aqueous dispersions, the problem remains of producing aqueous dispersions of high molecular weight water soluble polymers that have advantageously low bulk viscosities, high active solids content, minimal quantities of dilutive material, and that dissolve readily and can be prepared with a broad range of cationicity.

Summary of the Invention

This problem is solved in the present invention by providing novel aqueous dispersions of high molecular weight water-soluble or water-swellaable polymers, as well as processes for making and methods of using said aqueous dispersions. Accordingly, an aqueous dispersion of polymers is provided which comprises: (a) a first cationic water-soluble or water-swellaable polymer; and (b) at least one second water-soluble polymer different from said first polymer; and (c) a kosmotropic salt; and (d) a chaotropic salt, wherein the amounts of said (b), (c) and (d) are such that a homogeneous composition is obtained in the absence of said (b). In another embodiment, an aqueous dispersion of polymers is provided which comprises: (a) a first cationic water-soluble or water-swellaable polymer; and (b) at least one second water-soluble polymer different from said first polymer; and (c) a kosmotropic salt; and (d) an anionic organic salt, wherein the amounts of said (b), (c) and (d) are such that a homogeneous composition is obtained in the absence of said (b).

In another embodiment, an aqueous dispersion of polymers is provided which is comprised of (a) a discontinuous phase containing polymer that is comprised predominately of a first cationic water-soluble or water-swellaable polymer having at least one recurring unit of the formula (I),

(I)



wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is a methyl, ethyl or propyl group, X is a counterion, and R_2 , R_3 , and R_4 together contain a total of at least 4 carbon atoms; and (b) at least one second water-soluble polymer different from said first polymer.


In another embodiment, an aqueous dispersion of polymers is provided which comprises: (a) a first cationic water-soluble or water-swellaable polymer having at least one recurring unit of the formula (I), wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is an alkyl or substituted alkyl group having from 1 to 10 carbons, or an aryl or substituted aryl group having from 6 to 10 carbons, X is a counterion, and R_2 , R_3 , and R_4 together contain a total of at least 4 carbon atoms; and (b) at least one second water-soluble polymer different from said first polymer, wherein a homogeneous composition is obtained in the absence of said (b).

In another embodiment, a process for making an aqueous dispersion of polymers is provided which comprises polymerizing vinyl-addition monomers to form an aqueous dispersion comprised of a first cationic water-soluble or water-swellaable polymer, wherein said polymerizing is carried out in the presence of an aqueous composition comprised of (a) at least one second water-soluble polymer different from said first polymer; (b) a kosmotropic salt; and (c) a chaotropic salt, wherein the amounts of said (a), (b) and (c) are such that a homogeneous composition is obtained if said polymerizing is carried out in the absence of said (a).

In another embodiment, a process for making an aqueous dispersion of polymers is provided which comprises polymerizing vinyl-addition monomers to form an aqueous dispersion comprised of a first cationic water-soluble or water-swella-
 5 ble polymer, wherein said polymerizing is carried out in the presence of an aqueous composition comprised of (a) at least one second water-soluble polymer different from said first polymer; (b) a kosmotropic salt; and (c) of an anionic organic salt, wherein the amounts of said (a), (b) and (c) are such that a homogeneous composition is obtained if said polymerizing is carried out in the absence of said (a).

10 In another embodiment, a process for making an aqueous dispersion of polymers is provided which comprises polymerizing vinyl-addition monomers comprised of at least one monomer of the formula (II) to form an aqueous dispersion comprised of a first cationic water-soluble or water-swella-
 ble polymer,

(II)



wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is a methyl, ethyl or propyl group, X is a counterion, and R_2 , R_3 , and R_4 together contain a total of at least 4 carbon atoms; and wherein said polymerizing
 20 is carried out in the presence of an aqueous composition comprised of at least one second water-soluble polymer different from said first polymer.

In another embodiment, a process for making an aqueous dispersion of polymers is provided which comprises polymerizing vinyl-addition monomers comprised of at least one monomer of the formula (II) to form an aqueous dispersion comprised of a first water-

soluble or water-swellable cationic polymer, wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is an alkyl or substituted alkyl group having from 1 to 10 carbons, or an aryl or substituted aryl group having from 6 to 10 carbons, X is a counterion, and R_2 , R_3 , and R_4 together contain a total of at least 4 carbon atoms; and wherein said polymerizing is carried out in the presence of an aqueous composition comprised of an amount of at least one second water-soluble polymer different from said first polymer; and wherein said amount of said second polymer is such that a homogeneous composition is obtained if said polymerizing is carried out in the absence of said second polymer.

In another embodiment, a process for blending two or more aqueous dispersions is provided, comprising intermixing (a) a first aqueous dispersion of a water-soluble or water-swellable polymer with (b) a second aqueous dispersion of a water-soluble or water-swellable polymer, wherein said (a) is different from said (b), to form a third aqueous dispersion.

In another embodiment, a method of dewatering a suspension of dispersed solids is provided which (a) intermixing an aqueous dispersion of polymers, or aqueous admixture thereof, in an amount effective for dewatering, with a suspension of dispersed solids, and (b) dewatering said suspension of dispersed solids, said aqueous dispersion being comprised of (i) a first cationic water-soluble or water-swellable polymer; and (ii) at least one second water-soluble polymer different from said first polymer; and (iii) a kosmotropic salt; and (iv) a chaotropic salt, wherein the amounts of said (ii), (iii) and (iv) are such that a homogeneous composition is obtained in the absence of said (ii).

In another embodiment, a method of dewatering a suspension of dispersed solids is provided which comprises (a) intermixing an aqueous dispersion of polymers, or aqueous admixture thereof, in an amount effective for dewatering, with a suspension of dispersed solids, and (b) dewatering said suspension of dispersed solids, said aqueous dispersion being comprised of (i) a first cationic water-soluble or water-swellable polymer; and (ii) at least one second water-soluble polymer different from said first polymer; and (iii) a kosmotropic salt; and (iv) an anionic organic salt, wherein the amounts of said (ii), (iii) and (iv) are such that a homogeneous composition is obtained in the absence of said (ii).

In another embodiment, a method of dewatering a suspension of dispersed solids is provided which comprises (a) intermixing an aqueous dispersion of polymers, or aqueous admixture thereof, in an amount effective for dewatering, with a suspension of dispersed solids, and (b) dewatering said suspension of dispersed solids, said aqueous dispersion

being comprised of (i) a discontinuous phase containing polymer that is comprised predominately of a first cationic water-soluble or water-swella-
ble polymer having at least one recurring unit of the formula (I), wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl,
5 or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is a methyl, ethyl or propyl group, X is a counterion, and R_2 , R_3 , and R_4 together contain a total of at least 4 carbon atoms; and (ii) at least one second water-soluble polymer different from said first polymer.

In another embodiment, a method of dewatering a suspension of dispersed solids is provided which comprises (a) intermixing an aqueous dispersion of polymers, or aqueous
10 admixture thereof, in an amount effective for dewatering, with a suspension of dispersed solids, and (b) dewatering said suspension of dispersed solids, said aqueous dispersion being comprised of (i) a first cationic water-soluble or water-swella-
ble polymer having at least one recurring unit of the formula (I), wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a
15 methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is an alkyl or substituted alkyl group having from 1 to 10 carbons, or an aryl or substituted aryl group having from 6 to 10 carbons, X is a counterion, and R_2 , R_3 , and R_4 together contain a total of at least 4 carbon atoms; and (ii) at least one second water-soluble polymer different from
20 said first polymer, wherein a homogeneous composition is obtained in the absence of said (ii).

In another embodiment, a process for producing substantially dry water-soluble or water-swella-
ble vinyl-addition polymer particles is provided which comprises (a) spray-drying a vinyl-addition polymer-containing aqueous dispersion into a gas stream with a residence
25 time of about 8 to about 120 seconds and at an outlet temperature of about 70° C to about 150° C and (b) collecting resultant polymer particles.

In another embodiment, substantially dry water-soluble or water-swella-
ble polymer particles are provided which are comprised of (a) a first cationic water-soluble or water-swella-
ble polymer; and (b) at least one second water-soluble polymer different from said
30 first polymer; and (c) a kosmotropic salt; and (d) a chaotropic salt, wherein about 90% or more of said polymer particles each individually contains both said (a) and said (b), said particles having a bulk density of about 0.4 grams per cubic centimeter to about 1.0 grams per cubic centimeter.

In another embodiment, there is provided a method comprising (a) intermixing a composition comprising substantially dry water-soluble or water-swella-
ble polymer particles comprised of (i) a first cationic water-soluble or water-swella-
35 ble polymer; and (ii) at least

one second water-soluble polymer different from said first polymer; and (iii) a kosmotropic salt; and (iv) a chaotropic salt, wherein about 90% or more of said polymer particles each individually contains both said (i) and said (ii), said particles having a bulk density of about 0.4 grams per cubic centimeter to about 1.0 grams per cubic centimeter, with water to form an aqueous polymer admixture, (b) intermixing said aqueous polymer admixture, in an amount effective for dewatering, with a suspension of dispersed solids, and (c) dewatering said suspension of dispersed solids.


In another embodiment, there is provided a method comprising (a) intermixing a composition comprising substantially dry water-soluble or water-swellaable polymer particles comprised of (i) a first cationic water-soluble or water-swellaable polymer; and (ii) at least one second water-soluble polymer different from said first polymer; and (iii) a kosmotropic salt; and (iv) an anionic organic salt, wherein about 90% or more of said polymer particles each individually contains both said (i) and said (ii), said particles having a bulk density of about 0.4 grams per cubic centimeter to about 1.0 grams per cubic centimeter, with water to form an aqueous polymer admixture, (b) intermixing said aqueous polymer admixture, in an amount effective for dewatering, with a suspension of dispersed solids, and (c) dewatering said suspension of dispersed solids.

In another embodiment, there is provided a method comprising (a) intermixing a composition comprising substantially dry water-soluble or water-swellaable polymer particles comprised of (i) a first cationic water-soluble or water-swellaable polymer having at least one recurring unit of the formula (I), wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is an alkyl or substituted alkyl group having from 1 to 10 carbons, or an aryl or substituted aryl group having from 6 to 10 carbons, X is a counterion, and R_2 , R_3 , and R_4 together contain a total of at least 4 carbon atoms; and (ii) at least one second water-soluble polymer different from said first polymer, wherein about 90% or more of said polymer particles each individually contains both said (i) and said (ii), said particles having a bulk density of about 0.4 grams per cubic centimeter to about 1.0 grams per cubic centimeter, with water to form an aqueous polymer admixture, (b) intermixing said aqueous polymer admixture, in an amount effective for dewatering, with a suspension of dispersed solids, and (c) dewatering said suspension of dispersed solids.


Detailed Description of Preferred Embodiments

The aqueous dispersions of the instant invention contain a first cationic water-soluble or water-swellaible polymer, preferably a vinyl-addition polymer. The cationic charge of said first cationic polymer may vary over a broad range by containing from about 1% to about 100% cationic recurring units, preferably about 5% or greater, more preferably about 10% or greater, even more preferably about 20% or greater, most preferably about 30% or greater, preferably about 90% or less, more preferably about 80% or less, most preferably about 70% or less, by mole based on total moles of recurring units in said first cationic polymer. Cationic recurring units may be formed by post-reaction of polymer, but are preferably formed by polymerization of cationic monomers. Cationic monomers may include any cationic monomer, including diallyldialkylammonium halide, cationic (meth)acrylates, and cationic (meth)acrylamides commonly used in preparing water-soluble polymers, preferably diallyldimethylammonium halide, as well as acid and quaternary salts of dialkylaminoalkyl(alk)acrylate and dialkylaminoalkyl(alk)acrylamide. Cationic recurring units may be formed by the polymerization of quaternizable monomers such as dialkylaminoalkyl(alk)acrylate or dialkylaminoalkyl(alk)acrylamide, followed by acidification or quaternization. Most preferably, the first cationic polymer contains cationic recurring units of the formula (I), preferably formed by polymerization of the corresponding monomers of the formula (II):

(I)



(II)



5 wherein R_1 is H or CH_3 , A is O or NH, B is alkylene or branched alkylene or oxyalkylene having from 1 to 5 carbons, R_2 and R_3 are each individually methyl, ethyl, or propyl, R_4 is an alkyl or substituted alkyl group having from 1 to 10 carbon atoms, or an aryl or substituted aryl group having from 6 to 10 carbon atoms, X is a counterion, and R_2 , R_3 and R_4 together contain at least a total of 4 carbon atoms, preferably at least 5 carbon atoms.

10 In certain preferred embodiments, R_4 is a methyl, ethyl or propyl group. In other preferred embodiments, R_4 is an alkyl or substituted alkyl group having from 4 to 10 carbon atoms. In other preferred embodiments, R_4 is benzyl. Preferably, X is chloride, bromide, iodide, methylsulfate, or ethylsulfate.

The first cationic water-soluble or water-swellaable polymer may be a copolymer and

15 may contain other cationic recurring units or nonionic recurring units. Nonionic recurring units may be formed from water-soluble monomers such as N-vinylpyridine, N-vinylpyrrolidone, hydroxyalkyl(meth)acrylates, etc., preferably (meth)acrylamide, or may be formed from hydrophobic monomers having low water-solubility, so long as the inclusion of the poorly water-soluble, e.g. hydrophobic, recurring units does not render the resulting

20 polymer water-insoluble or water-nonswellable. The first cationic polymer may contain amounts of recurring units of water-soluble non-ionic monomers ranging from 0% to about 99%, preferably about 10% or greater, more preferably about 20% or greater, most preferably about 30% or greater; preferably about 90% or less, more preferably about 80% or less, most preferably about 70% or less, by mole based on total moles of recurring units

in said polymer. The hydrophobic monomers may be hydrocarbon monomers e.g. styrene, butadiene, 1-alkene, vinyl cyclohexane, etc., other vinyl monomers such as vinyl halide, other primarily aliphatic or aromatic compounds with polymerizable double bonds, or monomers with only moderate water-solubility such as acrylonitrile. Preferably, the hydrophobic monomers are alkyl (alk)acrylates or aryl (alk)acrylates in which the alkyl or aryl groups contain about 1-12 carbon atoms, such as methyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate, butyl (meth)acrylate, hexyl (meth)acrylate, ethylhexyl (meth)acrylate, isoalkyl (meth)acrylate, cyclohexyl (meth)acrylate, or aromatic (meth)acrylate, or alkyl or aryl (alk)acrylamides in which the alkyl or aryl groups contain about 1-12 carbon atoms, such as methyl (meth)acrylamide, ethyl (meth)acrylamide, t-butyl (meth)acrylamide, dimethyl (meth)acrylamide, hexyl (meth)acrylamide, ethylhexyl (meth)acrylamide, isoalkyl (meth)acrylamide, cyclohexyl (meth)acrylamide, or aromatic (meth)acrylamide. The first cationic water-soluble or water-swellaable polymer may contain amounts of hydrophobic non-ionic recurring units ranging from 0% to about 15%, preferably about 2% to about 10%, by mole based on total moles of recurring units in said polymer. Although hydrophobic recurring units may be dilutive of the polymer effect in certain applications, inclusion in controlled amounts may advantageously affect a particular characteristic of the aqueous dispersion, e.g. solubility rate, bulk viscosity, cost, ease of processing, performance, etc. Depending on the specific embodiment, it may be preferable for the polymer to be devoid of hydrophobic recurring units, or to contain chosen amounts of hydrophobic recurring units so as to achieve an advantageous effect without disadvantageously increasing the dilutive effect.

The amount of the first cationic water-soluble or water-swellaable polymer in the aqueous dispersion is as high as practicable, taking into account the effect of high solids on bulk viscosity, preferably about 5% or greater, more preferably about 10% or greater, most preferably about 20% or greater, by weight based on the total weight of the aqueous dispersion. Generally, the solids are not increased above an amount which increases the bulk viscosity to an impractical level. Practically, the amount of first cationic polymer in the aqueous dispersion is about 75% or less, preferably about 60% or less, more preferably about 50% or less, by weight based on total weight. The weight average molecular weight of the first cationic polymer in the aqueous dispersion is not critical and depends on the application, but is generally higher than about 1,000,000, preferably greater than about 2,000,000, more preferably greater than about 5,000,000, and most preferably greater than about 10,000,000. Molecular weights of polymers are weight average and may be determined by means known to those skilled in the art, preferably by light scattering.

The aqueous dispersions of the instant invention are generally comprised of a discontinuous phase of small aqueous droplets, containing polymer that is comprised predominately of the first cationic water-soluble or water-swellaable polymer, that are dispersed in the aqueous continuous phase, although of course minor amounts of said first polymer may be found in the continuous phase. Thus, the first cationic water-soluble or water-swellaable polymer generally constitutes more than 50%, preferably more than 75%, of the polymer in a typical small aqueous droplet. The amount of first cationic polymer in the discontinuous and continuous phases may be determined by known analytical techniques e.g. Raman microscopy. Although large aqueous droplets or gel particles may be formed by adding dry or gel polymer to the other components as in U.S. Patent No. 4,673,704 and EP 0 170 394 A2, the aqueous dispersions of the instant invention are preferred because it is generally more desirable for the first cationic polymer to be in the form of small droplets which are generally held suspended in a continuous matrix of the aqueous phase and do not generally rest substantially in contact with one another. Although aqueous dispersions prepared by polymerization of monomers as herein described may sometimes have an average droplet size of about 30 microns or more, the average droplet size is generally less than about 30 microns, preferably less than 20 microns, more preferably about 15 microns or less. Droplet size of a non-spherical droplet is the length along a major axis. Droplet size and shape tend to be a function of reactor conditions such as stirring rate, reactor configuration, type of stirrer, etc. Preferably, the size of the droplets is chosen by carrying out the polymerization in the presence of one or more insoluble polymeric seeds, said polymeric seeds being insoluble in an aqueous solution having the same inorganic salt concentration as said aqueous dispersion.

The aqueous dispersions of the instant invention contain a second water-soluble polymer, preferably a vinyl-addition polymer, that is different from and, preferably, incompatible with, said first water-soluble or water-swellaable cationic polymer. The second polymer is different from the first polymer when it can be distinguished from the first polymer on the basis of a particular physical characteristic e.g. chemical composition, charge, molecular weight, molecular weight distribution, distribution of recurring units along the polymer chain, etc., by known characterization methods e.g. spectroscopy, chromatography, etc. The second polymer is incompatible with the first polymer when solutions of the two polymers, at the concentrations present in the aqueous dispersion, do not form a homogenous mixture when blended, or do not form a homogenous mixture when one polymer is formed by polymerization of monomers in the presence of the other polymer.

The second, preferably cationic, water-soluble polymer in the aqueous dispersion of the instant invention is generally dissolved in the aqueous continuous phase, although of course minor amounts may be found in the discontinuous phase. The amount of second polymer in the discontinuous and continuous phases may be determined by known analytical techniques e.g. Raman microscopy. The second polymer may be any nonionic water-soluble polymer, preferably a polyalkyleneoxide, a polyvinylalcohol, polyvinylpyridine, polyvinylpyrrolidone, polyhydroxylalkyl(alk)acrylate, etc., most preferably poly(meth)acrylamide. Even more preferably, the second water-soluble polymer is cationic. The second polymer may be any cationic polymer, and the charge may vary over a broad range by containing about 1% to about 100% cationic recurring units, preferably about 10% or greater, more preferably about 20% or greater, even more preferably about 30% or greater, by mole based on total moles of recurring units in the polymer. Although in some cases the second cationic polymer may contain about 70% or less, or even about 50% or less, of cationic recurring units, preferably the second polymer is predominately cationic i.e. contains more than 50% cationic recurring units, by mole based on total moles of recurring units in the polymer; most preferably about 80% or greater of recurring cationic units, same basis. Cationic recurring units may be formed by polymerization of cationic monomers or by post-reaction of polymer as above, and may be a copolymer and may contain other cationic recurring units or nonionic recurring units as above. Preferred second cationic water-soluble polymers contain recurring units of diallyldialkylammonium halide, methyl chloride quaternary salt of dialkylaminoalkyl(alk)acrylate, dimethyl sulfate quaternary salt of dialkylaminoalkyl(alk)acrylate, methyl chloride quaternary salt of dialkylaminoalkyl(alk)acrylamide, or dimethyl sulfate quaternary salt of dialkylaminoalkyl(alk)acrylamide. Especially preferred second cationic water-soluble polymers contain recurring units of diallyldimethylammonium chloride, methyl chloride quaternary salt of dimethylaminoethyl(meth)acrylate, or dimethyl sulfate quaternary salt of dimethylaminoethyl(meth)acrylate. One or more second cationic polymers may be used.

Depending on the application, it may be preferable for the second polymer to be cationic in order to maximize the cationic charge density of the aqueous dispersion. Also, for embodiments which contain salt, it may be preferable for the second polymer to be cationic because cationic polymers are often more soluble in salt solution than nonionic polymers.

The amount of the second, preferably cationic, water-soluble polymer in the aqueous dispersion is generally chosen to control aqueous dispersion properties e.g. performance, bulk viscosity, charge, molecular weight, solubility rate, physical stability, e.g.

settling, etc. Generally, the amount of said second polymer is about 5% or greater, preferably about 10% or greater, more preferably about 20% or greater, most preferably about 30% or greater, by weight based on the amount of first cationic water-soluble polymer. Practically, the amount of second water-soluble polymer in the aqueous dispersion is 100% or less, preferably about 80% or less, more preferably about 50% or less, by weight based on the amount of first cationic water-soluble polymer. In certain preferred embodiments, the amounts of the first and second polymers are effective to form an aqueous dispersion. In some embodiments, an aqueous dispersion is not formed in the absence of the second polymer, and a homogeneous composition is obtained instead. Practically, the amount of first and second polymer may be found by routine experimentation, and different amounts will ordinarily be used depending on the identity of the first and second polymers, the total polymer solids level, the bulk viscosity, cost, ease of production, product performance, etc.

The weight average molecular weight of the second water-soluble polymer in the aqueous dispersion is also generally chosen to provide the most advantageous effect, e.g. bulk viscosity, performance, cost, etc., but is generally higher than about 10,000, preferably greater than about 50,000, more preferably greater than about 500,000, and most preferably greater than about 1,000,000. Molecular weights of polymers are weight average and may be determined by means known to those skilled in the art, preferably by light scattering. The second water-soluble polymer is primarily in the continuous phase of the aqueous dispersion, although of course minor amounts may be contained in the dispersed droplets. Preferably, the aqueous dispersions of the instant invention are heterogeneous compositions in which more than 50%, preferably about 75% or more, of the first cationic water-soluble or water-swellaable polymer is in the form of a discontinuous phase of aqueous droplets that are dispersed in an aqueous solution that is comprised of more than 50%, preferably about 75% or more, of the second, preferably cationic, water-soluble polymer.

The aqueous dispersions of the instant invention may contain a third water-soluble or water-swellaable polymer that is different from the first or second polymers. For instance, the third polymer may also be contained in droplets dispersed in the aqueous solution, in which case it may be described as discussed above for the first cationic polymer. The third polymer may also be dissolved in the aqueous solution along with the second polymer, in which case it may be described as discussed above for the second polymer. Preferably, the third polymer is cationic.

A third aqueous dispersion, containing three or more polymers, may be formed by blending first and second aqueous dispersions of the instant invention, wherein the first and

second aqueous dispersions are different from each other. Blending is generally carried out by intermixing the aqueous dispersions, typically with stirring. Blending may be advantageous to achieve a balance of properties exhibited by the individual aqueous dispersions, e.g. performance, charge, total polymer solids, cost, molecular weight, etc. Surprisingly, in many cases the blends are stable, e.g. remain in the form of aqueous dispersions having low bulk viscosity e.g. less than 10,000 centipoise for periods of one week or more, even when the salt or second polymer level in the blend is greatly different from the level needed to obtain a stable product for one or both of the dispersed polymers, if formulated alone. Also surprisingly, the bulk viscosity of the blend is often lower than the bulk viscosity of any of the individual aqueous dispersions.

The molecular weight of the aqueous dispersion, as that term is used herein, is simply the weight average molecular weight of the polymers contained therein, obtained by subjecting the entire dispersion to a suitable molecular weight characterization technique e.g. light scattering. Since the aqueous dispersion contains two or more different polymers, each of which may have a molecular weight and molecular weight distribution different from the other(s), the molecular weight distribution of the aqueous dispersion may be multimodal. The molecular weight of the aqueous dispersion is generally about 1,000,000 or greater, preferably greater than 2,000,000, more preferably about 3,000,000 or greater, most preferably about 5,000,000 or greater.

In some cases it may be more convenient to characterize the aqueous dispersion in terms of standard viscosity instead of by molecular weight. As used herein, "standard viscosity" is determined by: diluting an aqueous dispersion with water to form an aqueous admixture (in the case of water-swellaable polymers) or solution (in the case of water-soluble polymers) having a polymer concentration of about 0.2%; mixing together 8.0 g of this aqueous admixture or solution with 8.6 g of 2M NaCl; and then measuring the viscosity of the resultant mixture at 25°C on a rotating cylinder viscometer e.g. Brookfield Viscometer equipped with a UL adapter at 60 rpm. The standard viscosities of the aqueous dispersions of the instant invention are generally about 1.5 centipoise or greater, preferably about 1.8 centipoise or greater, more preferably about 2.0 centipoise or greater, most preferably about 2.5 centipoise or greater, depending on the application.

The aqueous dispersions of the instant invention may also be intermixed with water-in-oil emulsions or microemulsions of water-soluble polymers to form compositions which, though they contain oil, contain proportionately less oil than the water-in-oil emulsions or microemulsions from which they are derived. Consequently, these

compositions may advantageously produce less secondary pollution, have lower flammability, etc.

5 Certain embodiments of the instant invention require salt. Effective amounts of salt tend to reduce the bulk viscosity of the aqueous dispersion. The salt may be any inorganic salt, preferably a kosmotropic salt e.g. a chloride, sulfate, phosphate, or hydrogenphosphate salt, more preferably ammonium sulfate, sodium chloride, and sodium sulfate, most preferably sodium sulfate and ammonium sulfate. The counterion may be any counterion, e.g. Group IA and Group IIA metal ions, ammonium, etc., preferably ammonium, sodium, potassium and magnesium. Mixtures of salts may be used, and the amount of salt may be
10 chosen to achieve a desirable bulk viscosity or any other desirable effect. Since the salt may have a dilutive effect, in certain preferred embodiments the salt is only added in amounts so as to achieve a homogeneous composition in the absence of the second water-soluble polymer. In these embodiments, the aqueous dispersion is not formed by the action of the salt, but by the interaction of the first and second polymers. Effective or viscosity-reducing amounts of salt may be found through routine experimentation and are generally
15 chosen to reduce the bulk viscosity without causing precipitation of the polymer. In other preferred embodiments, the salt is only added in amounts so as to achieve a homogeneous composition in the absence of the first cationic polymer. In embodiments where salt is helpful but not necessary, salt levels may range upwards from 0%, preferably about 3% or greater, most preferably about 5% or greater, by weight based on total weight, depending
20 on the upper limit to solubility, because solubility of the salt in the aqueous dispersion is preferred. In embodiments where salt is necessary, salt levels are chosen to favorably influence product attributes such as cost, bulk viscosity, etc. and may range upwards from about 1%, preferably about 3% or greater, most preferably about 5% or greater, by weight
25 based on total weight, depending on the upper limit to solubility, because solubility of the salt in the aqueous dispersion is preferred. Frequently, no practical effect of the salt is observed above about 30%, so salt levels are generally about 30% or less, preferably about 25% or less, by weight based on total weight. Practically, the salt level may be determined by routine experimentation, e.g. balancing the tendency for positive product attributes e.g.
30 lower bulk viscosities resulting from higher salt levels, against the negative aspects of salt use e.g. cost and dilutive effect.

Surprisingly, it has been discovered that mixtures of chaotropic salts with kosmotropic salts, or anionic organic salts with kosmotropic salts, have a tendency to
35 reduce the bulk viscosity of the aqueous dispersion. In many cases, the salt mixture is more effective than either salt alone, on a weight basis. Useful chaotropic salts include

thiocyanates, perchlorates, chlorates, nitrates, bromides, iodides, and mixtures thereof, preferably sodium thiocyanate and sodium iodide. Useful anionic organic salts include anionic surfactants and anionic hydrotropic salts, preferably aryl and substituted aryl sulfonates having from 6 to 22 carbons, preferably 6 to 18 carbons, and alkyl and substituted alkyl sulfonates having from 2 to 22 carbons, preferably 4 to 18 carbons, and mixtures thereof. Especially preferred anionic organic salts are dialkylsulfosuccinates, diarylsulfosuccinates, benzenesulfonates, benzenedisulfonates, naphthalensulfonates, naphthalenedisulfonates, and mixtures thereof; 1,3-benzendisulfonates are most preferred. Counterions to the chaotropic and anionic organic salts may be any typical counterion, e.g. Group IA metal ions, ammonium, etc., preferably ammonium, sodium, and potassium. Effective or viscosity-reducing amounts of chaotropic and anionic organic salts may be found through routine experimentation and are generally chosen to reduce the bulk viscosity without causing precipitation of the polymer. In certain preferred embodiments, the amounts of chaotropic salt, or anionic organic salt, and kosmotropic salt are chosen such that a homogeneous composition is obtained in the absence of the second cationic polymer; i.e. the concentration of the salts is such that the first cationic polymer is not precipitated in the absence of the second cationic polymer. Generally, amounts of chaotropic, or anionic organic, salts are about 10% or less, preferably about 5% or less, and generally 0.5% or more, preferably 1% or more, by weight based on total weight. At very low chaotropic or anionic organic salt levels, the viscosity-reducing effect of the salt is negligible, whereas the salt may cause undesirable precipitation or layering at high levels of incorporation. To achieve a certain bulk viscosity, amounts of kosmotropic salts used with the chaotropic, or anionic organic salt, are generally less than when the kosmotropic salt is used alone, but still within the ranges given above for the use of inorganic or kosmotropic salts alone.

The aqueous dispersions of the instant invention generally have lower bulk viscosities than comparable aqueous dispersions. A comparable aqueous dispersion is generally one which is substantially identical in many functional aspects, but lacks a particular element of the instant invention. In general, the aqueous dispersions of the instant invention have lower bulk viscosities than comparable aqueous dispersions which have substantially the same polymer solids, cationic charge level and weight average molecular weight, but which lack an important feature of the instant invention e.g. lack a recurring unit of formula (I); lack the amount of recurring units of formula (I) found in the aqueous dispersions of the instant invention; not made by a process which comprises polymerizing vinyl-addition monomers comprised of at least one monomer of the formula (II); not made by a process which comprises polymerizing vinyl-addition monomers

comprised of the amount of monomers of the formula (II) used in the processes of the instant invention, etc. For instance, in a composition comprising an aqueous dispersion comprised of: (a) a discontinuous phase containing polymer that is comprised predominately of a first cationic water-soluble or water-swellaible polymer having at least one recurring unit of the formula (I), and (b) at least one second water-soluble polymer different from said first polymer, a comparable aqueous dispersion may be one which contains the same amount of each component, except the R_2 , R_3 and R_4 in the corresponding recurring formula (I) unit of the comparable aqueous dispersion together contain a total of 3 carbon atoms, instead of the 4 or more carbons in the corresponding recurring unit of formula (I) in the claimed aqueous dispersion.

Surprisingly, aqueous dispersions having formula (I) recurring units in which R_2 , R_3 and R_4 contain four or, preferably, five carbons generally have bulk viscosities which are dramatically lower than the bulk viscosities of aqueous dispersions that are substantially identical except that R_2 , R_3 and R_4 contain only three carbons. The bulk viscosity of aqueous dispersions is typically influenced by e.g. total polymer solids, salt level, polymer type, ratio of first cationic polymer to second cationic polymer, etc. as disclosed herein. Although aqueous dispersions having bulk viscosities of about 20,000 centipoise (cps) or more, or even about 200,000 cps or more may be suitable in certain circumstances, much lower bulk viscosities are generally preferred for ease of handling. Aqueous dispersions having bulk viscosities of about 20,000 centipoise (cps) or less, preferably about 10,000 cps or less, more preferably about 8,000 cps or less, even more preferably about 5,000 cps or less, most preferably about 2,500 cps or less, may be obtained by the practice of the instant invention. Bulk viscosity may be measured by any convenient method known to those skilled in the art, preferably a rotating cylinder viscometer as described in the Examples below.

Aqueous dispersions are preferred which have as many of the following advantageous attributes as possible: relatively high cationic polymer solids, preferably 20% or greater, more preferably 25% or greater, by weight based on total; high molecular weight, preferably 2,000,000 or greater, more preferably 5,000,000 or greater; reduced environmental impact (low VOC, substantially free of organic solvents and aromatic groups, e.g. aromatic- or benzyl-containing oils or recurring units); minimal levels of diluents (preferably, 20% or less of salt, by weight based on total, and polymer devoid or substantially free of hydrophobic recurring units); bulk viscosity about 2,000 cps or less; for recurring units based on formula (I), R_2 , R_3 and R_4 together containing a total of 5 carbons;

and superior or equivalent performance. Products having all of these attributes may be obtained by the practice of the present invention.

Aqueous dispersions of water-soluble polymers are preferably formed by polymerization of the corresponding monomers to form the first cationic water-soluble polymer, in the presence of at least one second cationic water-soluble polymer and, in certain embodiments, an inorganic salt. Polymerization may be effected by any initiating means, including redox, thermal or irradiating types. Examples of preferred initiators are 2,2'-azobis(2-amidino-propane)dihydrochloride (V-50), 2,2'-azobis(isobutyronitrile), sodium bromate/sulfur dioxide, potassium persulfate/sodium sulfite, and ammonium persulfate/sodium sulfite, as well as peroxy redox initiators e.g. those disclosed in U.S. 4,473,689. Initiator levels are chosen in a known manner so as to create polymers of the desired molecular weight. Amounts of chain transfer agents, e.g. isopropanol, lactic acid, mercaptoethanol, etc. and branching or crosslinking agents, e.g. methylenebisacrylamide may be added in a known manner to further adjust the properties of the first cationic water-soluble polymer. Depending on the production conditions, e.g. types and relative amounts of chain transfer agent and branching agent, water-swellaable or branched, water-soluble polymers may be formed. In general, the use of greater amounts of branching or crosslinking agent increases the tendency for the product to be water-swellaable instead of water-soluble, and increased amounts of chain transfer agent tend to reduce molecular weight. When chain transfer agent and branching agent are used together, water-swellaable products are more likely to be obtained at high branching agent and low chain transfer agent levels, whereas branched, water-soluble polymers may be obtained at high chain transfer and low branching agent levels. Components may be added at any time; e.g. all of the monomers may be present from the onset of the polymerization, or monomers may be added during the course of the polymerization. If salt is used, all of the salt may be present from the onset of the polymerization, or salt may be added during the course of the polymerization or after polymerization is complete. Likewise, polymerization parameters e.g. temperature and time may be chosen in a known manner, and may be varied during the course of the polymerization. Polymerization is generally effected in the presence of an inert gas, e.g. nitrogen. Conventional processing aids e.g. chelating agents, sequestrants, pH adjusters, etc. may be added as required.

The aqueous dispersions of the present invention have advantageous aspects in that they are preferably substantially free of dilutive substances such as surfactant, oil, hydrocarbon liquids, organic solvents, etc. Although viscosity-reducing additives e.g. glycerin, glycerol, alcohol, glycol, etc. may be present in the aqueous dispersions, amounts

should be 2% or less, more preferably 1% or less, most preferably 0.1% or less, in order to maintain the advantageous properties of the invention.

5 The aqueous dispersions of the instant invention may be homogenous in the absence of a particular component e.g., said second water-soluble polymer. Homogenous compositions are generally characterized as being clear or translucent, and are not aqueous dispersions because they do not contain dispersed droplets as described above. Depending on the embodiment, said first cationic water-soluble polymer or said second cationic water-soluble polymer is dispersion-creating in that aqueous dispersions are not obtained in the absence of an effective or dispersion-creating amount of the particular
10 component.

Waters used in the present invention may be from any source, e.g. process water, river water, distilled water, tap water, etc. Preferably, polymerizations are conducted in aqueous solutions that do not contain substantial amounts of materials which detrimentally affect the polymerization. Advantageously, the aqueous dispersions of the present invention
15 tend to dissolve quickly when diluted with water.

The aqueous dispersion of the instant invention may be dehydrated to increase the total polymer solids content, or to create substantially dry products. Any means known in the art e.g. stripping, spray drying, solvent precipitation, etc. may be used to reduce the water content. Surprisingly, partial dehydration may reduce the bulk viscosity of an
20 aqueous dispersion, in spite of the tendency for dehydration to increase polymer solids. Dehydration may be performed by heating, preferably under reduced pressure, although of course excessive heating may be detrimental to polymer properties. A substantially dry mass of polymer may be obtained by removal of water, and the mass may be comminuted to create a powdery, particulate, or granular product.

25 Surprisingly, substantially dry polymer products may be obtained by spray-drying the aqueous dispersions of the instant invention. Although oil-containing polymer emulsions and dispersions have been spray-dried, see e.g. U.S. Patent Application Serial No. 08/668,288 and references therein, spray-drying of aqueous dispersions, which are generally free of oil and surfactants, has not previously been reported. In accordance with the instant invention,
30 vinyl-addition polymer-containing aqueous dispersions may be sprayed-dried by a suitable means into a large chamber through which a hot gas is blown, thereby removing most or all of the volatiles and enabling the recovery of the dried polymer. Surprisingly, the means for spraying the aqueous dispersion into the gas stream are not particularly critical and are not limited to pressure nozzles having specified orifice sizes; in fact, any known spray-drying
35 apparatus may be used. For instance, means that are well known in the art such rotary

atomizers, pressure nozzles, pneumatic nozzles, sonic nozzles, etc. can all be used to spray-dry the aqueous dispersion into the gas stream. The feed rate, feed viscosity, desired particle size of the spray-dried product, droplet size of the aqueous dispersion, etc. are factors which are typically considered when selecting the spraying means. The size and shape of the chamber, the number and type of spraying means, and other typical operational parameters may be selected to accommodate dryer conditions using common knowledge of those skilled in the art.

Although closed cycle spray-dryers may be used, open cycle spray-drying systems are preferred. Gas flow may be cocurrent, countercurrent or mixed flow, cocurrent flow being preferred. The hot gas, or inlet gas, may be any gas that does not react or form explosive mixtures with the feed and/or spray-dried polymer. Suitable gases used as the inlet gas are gases known to those skilled in the art, including air, nitrogen, and other gases which will not cause undesirable polymer degradation or contamination, preferably gases containing about 20% or less oxygen, more preferably about 15% or less oxygen. Most preferably, inert gases such as nitrogen, helium, etc. that contain about 5% or less of oxygen should be used.

The dried polymer may be collected by various means such as a simple outlet, classifying cone, bag filter, etc., or the polymer may be subjected to further stages of drying, such as by fluid beds, or agglomeration. The means for collecting the dry polymer product is not critical.

There are four interrelated operating parameters in the instant spray-drying process: gas inlet temperature, gas outlet temperature, product volatiles and residence time in the dryer. The outlet temperature generally should be about 150°C or below, preferably about 120°C or below, more preferably less than 100°C, even more preferably about 95°C or below, most preferably about 90°C or below. The outlet temperature is generally about 70°C or higher, preferably about 75°C or higher. Therefore, outlet temperatures are generally about 70° C to about 150° C, preferably about 70° C to about 120° C, more preferably about 70° C to less than 100°C, even more preferably about 70° C to about 95° C, most preferably about 75°C to about 90°C. Outlet temperatures below about 70°C may be suitable in certain instances, though generally this is less preferred. For instance, at the cost of efficiency, spray drying could be carried out at long residence times, high gas flow rates and low outlet temperatures. Generally, the dryer should be operated at the lowest possible outlet temperature consistent with obtaining a satisfactory product.

The inlet temperature, the feed rate, and the composition of the aqueous dispersions may all affect outlet temperatures. These parameters may be varied to provide a desired outlet temperature. Feed rates are not critical, and generally will vary depending on the size of the

dryer and the gas flow rate. Inlet gas temperature is less critical than outlet gas temperature, and is generally about 140°C or above, preferably about 160°C or above. The inlet gas temperature is preferably about 200°C or below and more preferably about 180°C or below. Thus, preferred inlet gas temperature ranges from about 140°C to about 200°C, more preferably from about 160°C to about 180°C. Proper inlet gas temperatures tend to avoid product degradation on the high side and to avoid inadequate drying on the low side.

Residence time is a nominal value obtained by dividing the volume of the dryer by the volumetric gas flow. Residence time is generally at least about 8 seconds, preferably at least about 10 seconds. Residence time is generally no more than about 120 seconds, preferably no more than about 90 seconds, more preferably no more than about 60 seconds, and most preferably no more than about 30 seconds. Therefore, the general range of residence time is about 8 to about 120 seconds, preferably about 10 to about 90 seconds, more preferably about 10 to about 60 seconds, and most preferably about 10 to about 30 seconds. It is known to those skilled in the art that longer residence times are to be expected when larger dryers are used or when the dryer is run in a less efficient manner. For instance, at the cost of efficiency, longer residence times would be expected at very low inlet temperatures and slow gas flow rates. As a practical matter, the residence times useful in the present invention may vary from the values described above, depending on the size and type of spray dryer used, the efficiency at which it is operated, and other operational parameters. Thus, residence times specified herein may be modified to accommodate dryer conditions using common knowledge of those skilled in the art.

When produced according to the spray drying processes disclosed herein, polymer particles of the instant invention are generally about 10 microns or greater in diameter, preferably about 40 microns or greater, more preferably about 100 microns or greater, most preferably about 200 microns or greater. It is preferred that the polymer particles be non-dusting. Dusting and flow problems are typically exacerbated when the polymer particles are small, so larger polymer particles are generally desirable. However, very large particles may dissolve more slowly. Therefore, it is generally desirable for the polymer particles to be about 1200 microns or less in diameter, preferably about 800 microns or less in diameter, more preferably about 600 microns or less, most preferably about 400 microns or less. Generally, at least about 90% of the polymer particles range in size from about 10 microns to about 1200 microns, preferably at least about 95%, more preferably at least about 98%. The size of the polymer particles can be varied somewhat by altering the operational parameters e.g. spray configuration, aqueous dispersion viscosity, feed rate, etc. Particles may be substantially

spherical or non-spherical; "diameter" of a non-spherical particle is the dimension along a major axis.

Although in some cases the polymer particles are hollow, porous structures having at least one opening in their walls, it has been discovered that these features are not always necessary in order to obtain particles having desirable properties e.g. fast dissolution times. In many cases, the spray-drying parameters e.g. nozzle type, nozzle size, outlet temperature, etc. needed to produce particles that are hollow, porous structures having at least one opening in their walls are inconvenient or uneconomical, and it is advantageous to produce particles that lack some or all of these features.

The particles formed by the spray-drying processes of the instant invention may be screened to remove an oversize or undersize fraction. Oversize particles may be fragmented by e.g. grinding, whereas undersized particles are generally agglomerated. Sizes may be determined by methods known to those skilled in the art e.g. sieving, screening, light scattering, microscopy, microscopic automated image analysis, etc.

Surprisingly, the bulk densities of the spray-dried polymer particles of the instant invention are generally greater than the bulk densities of dry polymers prepared by precipitation of e.g. water-in-oil emulsions of the same polymer. Polymer particles having greater density may be advantageous because they occupy a smaller volume, resulting in e.g. lower shipping and storage costs. Whereas the densities of precipitated polymers are usually less than about 0.35 grams per cubic centimeter (g/cc), the bulk densities of the spray-dried polymer particles of the instant invention are generally about 0.35 g/cc or greater, preferably about 0.4 g/cc or greater, more preferably about 0.45 g/cc or greater, most preferably about 0.50 g/cc or greater. The bulk densities of the spray-dried polymer particles of the instant invention are generally about 1.1 g/cc or less, preferably about 1.0 g/cc or less, more preferably about 0.95 g/cc or less, most preferably about 0.90 g/cc or less. Therefore, the bulk densities of the spray-dried polymer particles of the instant invention generally range from about 0.35 to about 1.1 g/cc, preferably about 0.4 to about 1.0 g/cc, more preferably about 0.45 to about 0.95 g/cc, most preferably about 0.50 to about 0.90 g/cc.

Under the conditions of drying set forth herein, the polymer particles produced by the processes described herein are substantially dry. As used to describe the polymer produced herein, "substantially dry" generally means that the polymer contains about 12% or less volatiles, preferably about 10% or less by weight, based on the weight of the spray dried polymer. The polymer generally contains about 2% or more volatiles, preferably about 5% or more, by weight based on total weight, and most preferably contains from about 8% to about

10% volatiles by weight, same basis. The volatiles are measured by determining the weight loss on drying the polymer product at about 105°C for about 30 minutes.

It has also been discovered that agglomeration of the polymer particles of the instant invention may improve the flow properties and dissolution times of the polymers. Agglomeration is a known process for increasing particle size and various methods for agglomerating particles are known to those skilled in the art, e.g. "Successfully Use Agglomeration for Size Enlargement," by Wolfgang Pietsch, Chemical Engineering Progress, April 1996, pp. 29-45; "Speeding up Continuous Mixing Agglomeration with Fast Agitation and Short Residence Times," by Peter Koenig, Powder and Bulk Engineering, February 1996, pp. 67-84. Known agglomeration methods such as natural agglomeration, mechanical agglomeration, tumble or growth agglomeration, pressure agglomeration, binderless agglomeration, agglomeration with binders, etc. may be used to agglomerate the polymer particles of the instant invention. Agglomeration may optionally be followed by drying e.g. fluid bed drying, to remove binder e.g. water. Pressure agglomeration is preferred, and mechanical agglomeration using a water binder, followed by fluid bed drying is most preferred.

The agglomerates formed by agglomerating the polymer particles of the instant invention tend to have improved flow properties and faster dissolution times when compared to the unagglomerated polymer particles. Preferably, the agglomerates are non-dusting. Typically, about 90% of the agglomerates of the instant invention have an agglomerate size of about 120 microns or greater, preferably about 160 microns or greater, more preferably about 200 microns or greater, most preferably about 300 microns or greater. Generally, about 90% of the agglomerates have an agglomerate size of about 1500 microns or less, preferably about 1200 microns or less, more preferably about 1100 microns or less, most preferably about 1000 microns or less. Thus, about 90%, preferably 95%, of the agglomerates have a size in the range of about 120 to about 1500 microns, preferably about 160 microns to about 1200 microns, more preferably about 200 microns to about 1100 microns, most preferably about 300 microns to about 1000 microns. Usually, at least about 5% of the agglomerates, preferably at least about 10%, most preferably at least about 15%, are larger than about 900 microns. The agglomerates formed by agglomerating the spray-dried particles of the instant invention may be screened to remove an oversize or undersize fraction. Preferably, agglomerates larger than about 1200 microns and smaller than about 175 microns are removed by e.g. screening. Oversize agglomerates are generally fragmented by e.g. grinding, whereas undersized agglomerates are generally recycled into the agglomerator.

The bulk density values of the agglomerates of the instant invention tend to be lower than the bulk density values of the spray-dried particles from which they are formed. The bulk

densities of the agglomerates of the instant invention are generally about 0.35 g/cc or greater, preferably about 0.4 g/cc or greater, more preferably about 0.45 g/cc or greater, most preferably about 0.50 g/cc or greater. The bulk densities of the agglomerates of the instant invention are generally about 1.0 g/cc or less, preferably about 0.95 g/cc or less, more preferably about 0.90 g/cc or less, most preferably about 0.85 g/cc or less. Therefore, the bulk densities of the agglomerates of the instant invention generally range from about 0.35 to about 1.0 g/cc, preferably about 0.4 to about 0.95 g/cc, more preferably about 0.45 to about 0.90 g/cc, most preferably about 0.50 to about 0.85 g/cc.

In order to obtain agglomerates of a preferred size, it is preferred that the polymer particles themselves be of such a size that they are agglomerable. Agglomeration obviously tends to multiply the average particle size, so that it is frequently easier to cause large increases in particle size than it is to cause small increases in particle size. Therefore, to produce agglomerates of a preferred size or size range, it is generally preferred to agglomerate particles that are much smaller than the desired agglomerate size, rather than particles that are only slightly smaller. Agglomerable particles are generally those that may be conveniently agglomerated to produce agglomerates having a preferred size. It is possible, but less preferred, to agglomerate larger particles to produce agglomerates that are larger than desired, then remove the oversize agglomerates as described above.

The substantially dry polymer particles and agglomerates of the present invention are generally comprised of the polymer that was contained in the aqueous dispersion that was spray-dried, as discussed hereinabove.

Spray-drying of the aqueous dispersions of the instant invention is advantageous because typically 90% or greater, preferably 95% or greater, most preferably substantially all, of the resultant spray-dried polymer particles each individually contains two or more water-soluble or water-swelling vinyl-addition polymers, so that stratification effects may be minimized. Stratification may occur when two different dry polymers having differing particle sizes or particle size distributions are blended together because of the tendency for the larger particles to settle towards the bottom of the container. Stratification on storage may affect blend product performance as the top of the container tends to become enriched in the polymer having the smaller particle size. For obvious reasons, changes in product performance as a function of storage depth are to be avoided, and it is generally preferred that each polymer in a blend be of similar particle size, see e.g. EP 479 616 A1 and U.S. Patent No. 5,213,693. A dry blend of the two different polymers is likely to exhibit greater stratification than a dry blend obtained by spray-drying the instant aqueous dispersions because the majority of the spray-dried polymer particles of the instant invention each individually contains two or more water-soluble or water-

swellable vinyl-addition polymers. Surprisingly, the spray-dried aqueous dispersions of the instant invention tend to dissolve faster than polymers obtained by spray-drying conventional water-in-oil emulsions of similar polymers.

5 A suspension of dispersed solids may be dewatered by a method which comprises (a) intermixing an effective amount of an aqueous dispersion of polymers, or aqueous admixture thereof, with a suspension of dispersed solids, and (b) dewatering said suspension of dispersed solids. Substantially dry polymers derived from the aqueous dispersions of the instant invention as described above may also be used to dewater suspended solids. For instance, a suspension of dispersed solids may be dewatered by
10 a method which comprises (a) intermixing an effective amount of a substantially dry water-soluble or water-swellable polymer, or aqueous admixture thereof, with a suspension of dispersed solids, and (b) dewatering said suspension of dispersed solids. Preferably, an aqueous admixture of the dry polymer or aqueous dispersion is prepared by intermixing the dry polymer or aqueous dispersion with water, more preferably by dissolving the dry
15 polymer or aqueous dispersion in water to form a dilute polymer solution. Effective amounts of dry polymer or aqueous dispersion are determined by methods known in the art, preferably by routine laboratory or process experimentation.

Examples of suspensions of dispersed solids which may be dewatered by means of the instant invention are municipal and industrial waste dewatering, clarification and
20 settling of primary and secondary industrial and municipal waste, potable water clarification, etc. Because of the advantageous aspects of the invention e.g. substantially oil-free, minimum amounts of inactive diluents, little or no surfactant, etc., the polymers may be especially well-suited to situations where part or all of the dewatered solids or clarified water is returned to the environment, such as sludge composting, land application of sludge,
25 pelletization for fertilizer application, release or recycling of clarified water, papermaking, etc. Other applications which may benefit from the advantageous aspects of the instant inventions include soil amendment, reforestation, erosion control, seed protection/growth, etc., where the aqueous dispersion or dry polymer, preferably an aqueous admixture thereof, is advantageously applied to soil.

30 Other examples of suspensions of dispersed solids which may be dewatered by means of the instant invention are found in the papermaking area, e.g. the aqueous dispersions or dry polymer may be used as retention aids, drainage aids, formation aids, washer/thickener/drainage production aid (DNT deink application), charge control agents, thickeners, or for clarification, deinking, deinking process water clarification, settling, color
35 removal, or sludge dewatering. The polymers of the instant invention may also be used in

oil field applications such as petroleum refining, waster clarification, waste dewatering and oil removal.

Dewatering and clarification applications for the aqueous dispersions and dry polymers of the instant invention may also be found in the food processing area, including waste dewatering, preferably waste dewatering of poultry beef, pork and potato, as well as sugar decoloring, sugar processing clarification, and sugar beet clarification.

Mining and mineral applications for the aqueous dispersions and dry polymers of the instant invention include coal refuse dewatering and thickening, tailings thickening, and Bayer process applications such as red mud settling, red mud washing, Bayer process filtration, hydrate flocculation, and precipitation.

Biotechnological applications for the aqueous dispersions and dry polymers of the instant invention include dewatering and clarification of wastes and preferably, dewatering and clarification of fermentation broths.

The aqueous dispersions of the instant invention may be employed in the above applications alone, in conjunction with, or serially with, other known treatments.

All patents, patent applications, and publications mentioned above are hereby incorporated herein by reference. Unless otherwise specified, all percentages mentioned herein are understood to be on a weight basis.

The Standard Viscosity (SV) values in the following Examples were determined by mixing together 8.0 g of a 0.2 wt. % polymer solution in water and 8.6 g of 2M NaCl, then measuring the viscosity of the resultant solution at 25°C on a Brookfield Viscometer equipped with a UL adapter at 60 rpm. Molecular weights were determined by high performance size exclusion chromatography using a light scattering detector.

The bulk density of polymer particles and agglomerates was determined by adding the particles or agglomerates to a suitable preweighed measuring container and "tapping" or slightly agitating the container to cause the particles or agglomerates to settle. The volume of the polymer was then read from the measuring container, the measuring container weighed, and the bulk density calculated in units of grams per cubic centimeter (g/cc).

EXAMPLE 1

A suitable vessel equipped with a mechanical stirrer, reflux condenser, and a nitrogen inlet tube was charged with 17.10 parts deionized water and 9 parts of a 40% aqueous solution of the polymer obtained by polymerizing the methyl chloride quaternary salt of dimethylaminoethylmethacrylate (poly(DMAEM.MeCl)), weight average molecular

weight about 200,000. After completion of dissolution, 7.08 parts of a 53.64% aqueous solution of acrylamide (AMD), and 14.56 parts of a 72.80% solution of the dimethyl sulfate salt of diethylaminoethylacrylate (DEAEA.DMS) were added and mixed. To this mixture, 8.1 parts ammonium sulfate, 0.7 parts citric acid, and 2.02 parts of a 1% solution of chelant ethylenediaminetetraacetic acid tetrasodium salt (EDTA) were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 1.44 parts of 1% aqueous solution of 2,2'-azobis(2-amidino-propane)dihydrochloride (V-50). The reaction mixture was heated to 40° C for 2 hours and then raised to 50°C and held for an additional 8 hours. The conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity (BV) of the dispersion was 2250 centipoise (cps) showing preferable fluidity as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25° C. The dispersion was dissolved to give a standard viscosity (SV) of 2.56 cps.

EXAMPLES 2-8

Additional aqueous dispersions were prepared in the same manner as Example 1, showing the effect of various polymer and ammonium sulfate salt levels on bulk viscosity as shown in Table 1.

Table 1

		FIRST	SECOND			
	% TOTAL	POLYMER	POLYMER	%	BV	SV
Example No.	SOLIDS	% SOLIDS	% SOLIDS	SALT	(cps)	(cps)
1	30	24	6	13.5	2,250	2.56
2	30	24	6	12.5	6,600	2.2
3	30	24	6	13	6,000	2.37
4	30	24	6	13.5	2,960	2.3
5	30	24	6	13.5	2,300	2.35

6	30	25	5	13.5	2,640	2.61
7	30	24	6	14	3,470	2.39
8	30	24	6	15	7,080	2.17

EXAMPLE 9

A suitable vessel equipped with a mechanical stirrer, reflux condenser, thermocouple and a nitrogen inlet was charged with 72.60 parts of deionized water and 30.8 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 222,600. After dissolution was complete, 24.37 parts of a 53.33% aqueous solution of acrylamide and 45.93 parts of a 79% aqueous solution of DEAEA.DMS were added and mixed. To this mixture, 31.9 parts ammonium sulfate, 2.57 parts citric acid, and 6.9 parts of 1% solution of EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 4.93 parts of 1% solution of V-50. The reaction mixture was heated to 40°C for 2 hours and then raised to and held at 50°C for 4 hours. The overall conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 1460 cps showing preferable fluidity as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25°C. The dispersion was dissolved to give a SV of 2.40 cps.

EXAMPLES 10-33

Additional aqueous dispersions were prepared in the same manner as Example 9 demonstrating the effect of total polymer solids, ratio of first cationic to second cationic polymer, second cationic polymer molecular weight, and ammonium sulfate salt level on the bulk viscosity (BV) of the aqueous dispersion, as shown in Table 2.

Table 2

		FIRST	SECOND	SECOND			
EXAMPLE	% TOTAL	POLYMER	POLYMER	POLYMER	%	BV	SV
NO.	SOLIDS	% SOLIDS	% SOLIDS	MW	SALT	(cps)	(cps)
9	28	22.4	5.6	222,600	14.5	1,460	2.40
10	28	22.4	5.6	194,000	14.5	2,250	2.52
11	28	22.4	5.6	199,300	14.5	1,440	2.52
12	28	22.4	5.6	172,870	14.5	2,940	2.61
13	28	22.4	5.6	221,500	14.5	1,970	2.52
14	28	22.4	5.6	159,000	14.5	2,740	2.59
15	28	22.4	5.6	145,000	14.5	2,920	2.65
16	28	22.4	5.6	199,300	14.5	2,150	2.86
17	30	24	6	242,900	13.5	2,620	2.49
18	30	24	6	230,600	13.5	3,710	2.4
19	30	24	6	230,600	14	2,200	2.39
20	30	24	6	230,600	14.5	1,800	2.54
21	30	24	6	230,600	15	3,260	2.49
22	28	22.4	5.6	230,600	15	982	2.49
23	28	22.4	5.6	230,600	15.5	900	2.45
24	28	23.5	4.5	230,600	15.5	1,380	2.77
25	27	22.66	4.34	230,600	15.5	1,600	2.61
26	27	22.66	4.34	230,600	16	1,770	2.82

27	30	24	6	230,600	14.5	1,770	2.43
28	28	22.4	5.6	230,600	15.5	1,820	2.56
29	28	22.4	5.6	230,600	16	3,120	2.44
30	28	23	5	230,600	15	1,620	2.5
31	28	23	5	230,600	15.5	962	2.67
32	28	23	5	230,600	16	1,500	2.59
33	28	22.4	5.6	230,600	15.5	1,260	2.51

EXAMPLE 34

This polymerization was carried out in the same manner as Example 9, except that a poly(DMAEM.MeCl) having a weight average molecular weight of about 395,000 was used. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this aqueous dispersion was about 5100 cps showing preferable fluidity as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25° C. The dispersion was dissolved to give a SV of 2.35 cps.

EXAMPLE 35

This polymerization was carried out in the same manner as Example 34, except that 2.46 parts of 10% glycerol solution was added. Polymerization proceeded smoothly. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 3700 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25°C showing improved fluidity. The bulk viscosity was greatly reduced relative to Example 34, demonstrating the viscosity-reducing effect of the glycerol additive. The dispersion was dissolved to give a SV of 2.35 cps.

EXAMPLE 36

5 A suitable vessel equipped with a mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube was charged with 39.73 parts deionized water and 30.1 parts of 41% poly(DMAEM.MeCl), weight average molecular weight about 395,000. After completion of dissolution, 23.77 parts of a 53.57% aqueous solution of acrylamide, 45.20 parts of an 80% aqueous solution of DEAEA.DMS and 38.7 parts of 1% aqueous solution of tertiary butyl acrylamide were added and mixed. To this mixture, 49.28 parts ammonium sulfate, 2.57 parts citric acid, and 3.45 parts of 2% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 2.46 parts of 2% V-50. The reaction mixture was raised to 40°C for 2 hours and then raised to 50°C for an additional 4 hours. The overall conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this aqueous dispersion was about 1900 cps as measured with a Brookfield Viscometer No. 4 spindle, 30 rpm at 25° C, showing improved fluidity compared to Example 34 and demonstrating the effect of incorporating hydrophobic recurring units of tertiary butyl acrylamide. The aqueous dispersion was dissolved to give a SV of 2.32 cps.

EXAMPLE 37

20 A suitable vessel equipped with a mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube was charged with 78.84 parts deionized water and 30.1 parts of 41% poly(DMAEM.MeCl), weight average molecular weight about 395,000. After completion of dissolution, 20.95 parts of a 53.57% aqueous solution of acrylamide, 42.73 parts of a 80% aqueous solution of DEAEA.DMS and 4.84 parts of a 80% aqueous solution of the benzyl chloride quaternary salt of dimethylaminoethyl acrylate (DMAEA.BzCl) were added and mixed. To this mixture, 49.28 parts ammonium sulfate, 2.57 parts citric acid, and 3.45 parts of 2% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 2.46 parts of 2% V-50. The reaction mixture was raised to 40°C for 2 hours, and then raised to and held at 50° C for 4 hours. The overall conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 3840 cps as measured with a Brookfield

Viscometer No. 4 spindle, 30 rpm at 25°C showing preferable fluidity. The dispersion was dissolved to give a SV of 2.14 cps.

EXAMPLE 38

5 A suitable vessel with an external jacket for heating or cooling was equipped with a mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube. The vessel was charged with 294.47 parts deionized water and 117.60 parts of 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 210,000. After completion of dissolution, 94.03 parts of a 52.77% aqueous solution of acrylamide and 173.18 parts of an 80% aqueous solution of DEAEA.DMS were added and mixed. To this mixture, 130.20 parts ammonium sulfate, 9.83 parts citric acid, and 13.17 parts of 2% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 7.53 parts of 1% V-50. The reaction mixture was heated to 40°C for 2 hours and then raised to and held at 50°C for 4 hours. The overall conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 760 cps as measured with a Brookfield Viscometer No. 4 spindle, 30 rpm at 25°C showing preferable fluidity. The dispersion was dissolved to give a SV of 2.52 cps.

EXAMPLE 39

20 A suitable vessel equipped with a mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube was charged with 63.18 parts deionized water and 30.8 parts of 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 230,600. After completion of dissolution, 27.96 parts of a 53.33% aqueous solution of acrylamide (AMD), 26.02 parts of a 80% aqueous solution of DEAEA.DMS and 16.94 parts of a 80% aqueous solution of the methyl chloride quaternary salt of dimethylaminoethylacrylate (DMAEA.MeCl) were added and mixed. To this mixture, 40.7 parts ammonium sulfate, 2.57 parts citric acid, and 6.9 parts of 1% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 4.93 parts of 1% V-50. The reaction mixture was raised to 40° C for 2 hours, and then raised to and held at 50° C for 4 hours. The overall conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 3840 cps as

measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25° C showing good fluidity. The dispersion was dissolved to give a SV of 2.14 cps.

EXAMPLES 40-42

Polymerizations were carried out in the same manner as Example 39 except that the bulk viscosity was adjusted by varying the level of ammonium sulfate salt as shown in Table 3. These Examples demonstrate that aqueous dispersions having low bulk viscosities and high polymer solids may be prepared, wherein the first cationic polymer is a DMAEA.MeCl / DEAEA.DMS / AMD terpolymer.

Table 3

EXAMPLE NO.	% TOTAL SOLIDS	FIRST POLYMER % SOLIDS	SECOND POLYMER % SOLIDS	% SALT	BV (cps)	SV (cps)
39	28	22.4	5.6	18.5	2,620	2.99
40	28	22.4	5.6	18	4,310	2.96
41	28	22.4	5.6	19	1,820	2.65
42	28	22.4	5.6	19.5	2,000	2.62

EXAMPLE 43

A suitable vessel equipped with an external jacket for heating or cooling, a mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube was charged with 260.35 parts deionized water and 117.6 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 210,000. After completion of dissolution, 107.89 parts of a 52.77% aqueous solution of acrylamide, 99.35 parts of a 80% aqueous solution of DEAEA.DMS and 64.68 parts of a 80% aqueous solution of DMAEA.MeCl were added and mixed. To this mixture, 271.92 parts ammonium sulfate, 9.83

parts citric acid, and 13.17 parts of 2% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 7.53 parts of 2.5% V-50. The reaction mixture was raised to 40°C for 2 hours, and then raised to and held at 50° C for 4 hours. The overall conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 1240 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25° C showing good fluidity. The dispersion was dissolved to give a SV of 2.74 cps.

EXAMPLE 44

A suitable vessel equipped with a mechanical stirrer, reflux condenser, and nitrogen inlet tube was charged with 18.86 parts deionized water and 9 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 200,000. After completion of dissolution, 4.39 parts of a 53.64% aqueous solution of acrylamide and 15.19 parts of a 79.3% aqueous solution of DEAEA.DMS were added and mixed. To this mixture, 8.4 parts ammonium sulfate, 0.7 parts citric acid, and 2.02 parts of 1% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 1.44 parts of 1% V-50. The reaction mixture was raised to 40°C for 2 hours and then raised to and held at 50° C for 8 hours. The conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 850 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25° C showing preferable fluidity. The dispersion was dissolved to give a SV of 2.27 cps.

EXAMPLES 45-49

Additional aqueous dispersions were prepared in the same manner as Example 44, demonstrating the effect of ratio of first cationic to second cationic polymer and salt content on the bulk viscosity of the dispersion as shown in Table 4.

Table 4

EXAMPLE	% TOTAL	FIRST	SECOND			
NO.	SOLIDS	% SOLIDS	% SOLIDS	SALT	BV (cps)	SV (cps)
44	30	24	6	14	852	2.27
45	30	24	6	12	2,400	2.19
46	30	24	6	13	1,100	2.34
47	30	24	6	15	1,770	2.35
48	30	25	5	13	1,260	2.45
49	30	25	5	14	4,750	2.4
50	30	24	6*	14	780	2.2

*Molecular weight of second polymer was about 222,600.

EXAMPLE 51

A suitable vessel equipped with a mechanical stirrer, reflux condenser, and nitrogen inlet tube was charged with 92.9 parts deionized water and 30.1 parts of a 41% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 395,000. After completion of dissolution, 15.03 parts of a 53.57% aqueous solution of acrylamide and 51.53 parts of an 80% aqueous solution of DEAEA.DMS were added and mixed. To this mixture 22 parts of sodium sulfate, 2.57 parts citric acid, and 3.45 parts of 2% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 2.46 parts of 2% V-50. The reaction mixture was raised to 40°C for 2 hours and then raised to and held at 50° C for 4 hours. The overall conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 1100 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25°C. The dispersion

was dissolved to give a SV of 2.19 cps. This Example demonstrates the effectiveness of sodium sulfate.

EXAMPLE 52

5 A suitable vessel equipped with a mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube was charged with 17.57 parts deionized water and 9 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 200,000. After completion of dissolution, 4.77 parts of a 53.64% aqueous solution
10 of acrylamide, 12 parts of a 79.3% aqueous solution of DEAEA.DMS and 2.91 parts of an 80% aqueous solution of DMAEA.MeCl were added and mixed. To this mixture, 9.6 parts ammonium sulfate, 0.7 parts citric acid, and 2.02 parts of 1% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 1.44 parts of 1% V-50. The
15 reaction mixture was raised to 40°C for 2 hours and then raised to and held at 50° C for 4 hours. The overall conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 800 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25° C showing good fluidity. The dispersion was dissolved to give a SV of 2.3 cps.

EXAMPLES 53-80

20 Polymerizations were carried out in the same manner as Example 52. The effect of total polymer solids, first cationic polymer composition (in terms of % AMD, %
25 DEAEA.DMS and % DMAEA.MeCl in monomer feed), ratio of first cationic to second cationic polymer, and ammonium sulfate salt content on the bulk viscosity of the aqueous dispersion is demonstrated as shown in Table 5.

Table 5

					FIRST	SECOND			
	%	%	%	% TOTAL	POLYMER	POLYMER	%	BV	SV
NO.	AMD	DEAEA.DMS	DMAEA.MeCl	SOLIDS	% SOLIDS	% SOLIDS	SALT	(cps)	(cps)
52	45	40	15	30	24	6	16	802	2.3
53	45	40	15	30	24	6	12	200,000+	2.4
54	45	40	15	30	24	6	13	30,900	2.35
55	45	40	15	30	24	6	14	4,410	2.35
56	45	40	15	30	24	6	15	1,080	2.42
57	45	40	15	30	24	6	17	1,820	2.32
58	45	40	15	30	24	6	18	15,800	2.2
59	45	40	15	30	24	6	19	200,000+	
60	45	40	15	30	25	5	15	1,940	2.45
61	45	40	15	30	25	5	16	1,260	2.49
62	45	40	15	30	25	5	17	6,010	2.4
63	45	35	20	30	24	6	15	3,120	2.19
64	45	35	20	30	24	6	16	1,340	2.24
65	45	35	20	30	24	6	17	1,140	2.32
66	45	30	25	30	24	6	16	170,000	1.82
67	45	30	25	30	24	6	17	1,890	2.44
68	45	30	25	30	24	6	18	1,400	2.35
69	45	20	35	29.3	23.44	5.86	18	200,000+	

70	45	20	35	29.3	23.44	5.86	18.5	2,900	2.4
71	45	20	35	29.3	23.44	5.86	19	6,600	2.24
72	45	10	45	28.5	22.8	5.7	18	200,000+	2.35
73	45	10	45	28.5	22.8	5.7	19	200,000+	2.34
74	45	10	45	28	22.4	5.6	19.6	200,000+	2.5
75	45	20	35	29	23.2	5.8	18	200,000+	2.2
76	45	20	35	29	23.2	5.8	18.5	5,540	2.27
77	45	20	35	29	23.2	5.8	19	3,570	2.47
78	45	20	35	28.5	23.2	5.8	18	6,350	2.35
79	45	20	35	28.5	23.2	5.8	18.5	3,060	2.4
80	45	20	35	28.5	23.2	5.8	19	200,000+	2.39

EXAMPLE 81

A suitable vessel equipped with a mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube was charged with 89 parts deionized water and 20.9 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 190,000. After completion of dissolution, 30.96 parts of a 52.77% aqueous solution of acrylamide and 21.38 parts of a 80% aqueous solution of DEAEA.DMS were added and mixed. To this mixture, 49.5 parts ammonium sulfate, 2.57 parts citric acid, and 2.34 parts of 1% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 3.34 parts of 1% V-50. The reaction mixture was raised to 40°C for 2 hours and then raised to and held at 50° C for 4 hours. The combined conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion

was about 280 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25° C showing good fluidity. The dispersion was dissolved to give a SV of 1.60 cps.

EXAMPLES 82-97

Polymerizations were carried out in the same manner as Example 81. The effect of chelant (EDTA) concentration, chain transfer agent (lactic acid), first cationic polymer composition (in terms of % AMD, % DEAEA.DMS, and % DMAEA.MeCl in monomer feed), ratio of first cationic to second cationic polymer, and ammonium sulfate salt content on standard viscosity and bulk viscosity are demonstrated as shown in Table 6.

Table 6

	%	%	%	%	FIRST	SECOND	%					
				TOTAL	POLYMER	POLYMER	LACTIC	EDTA	%	BV	SV	
NO.	AMD	DEAEA.DMS	DMAEA.MeCl	SOLIDS	% SOLIDS	% SOLIDS	ACID	(ppm)	SALT	(cps)	(cps)	
81	80	20		19	15.2	3.8	0	1400	22.5	280	1.6	
82	80	20		20	16	4	0	1400	20	142,000	1.82	
83	80	20		20	16	4	0	1400	22.5	840	1.6	
84	80	20		19	15.2	3.8	0.25	1400	22.5	200	2.05	
85	80	20		19	15.2	3.8	0.5	1400	22.5	100	1.67	
86	80	20		19	15.2	3.8	0.75	1400	22.5	200	1.87	
87	80	20		19	15.2	3.8	0	2000	22.5	280	1.61	
88	80	20		19	15.2	3.8	0	3000	22.5	4,800	1.81	
89	80	20		19	15.2	3.8	0.25	2000	22.5	270	1.99	
90	80	20		19	15.2	3.8	0.5	2000	22.5	2,000	2.47	
91	80	20		19	15.2	3.8*	0.5	2000	22.5	140	2.1	

92	80	20		19	15.2	3.8	0.5	2000	22.5	640	2.45
93	80	20		19	15.2	3.8	0.65	2000	22.5	360	2.4
94	80	20		19	15.2	3.8	0.75	2000	22.5	225	2.35
95	80	10	10	19	15.2	3.8	0	1400	22.5	760	2.09
96	80	10	10	19	15.2	3.8	0.25	1400	22.5	460	2.86
97	80	10	10	19	15.2	3.8	0.5	1400	22.5	340	2.74

*Molecular weight of second polymer was about 222,600.

EXAMPLE 98

A suitable vessel equipped with a mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube was charged with 87.97 parts deionized water and 20.9 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 190,000. After completion of dissolution, 33.99 parts of a 52.77% aqueous solution of acrylamide, 11.74 parts of a 80% aqueous solution of DEAEA.DMS and 7.64 parts of a 80% aqueous solution of DMAEA.MeCl were added and mixed. To this mixture, 49.5 parts ammonium sulfate, 2.57 parts citric acid, and 2.34g of 2% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 2.34 parts of 1% V-50. The reaction mixture was raised to 40°C for 2 hours and then raised to and held at 50°C for 4 hours. The overall conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 760 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25°C. The dispersion was dissolved to give a SV of 2.09 cps.

EXAMPLES 99-100

Polymerizations were carried out in the same manner as Example 97. The effect of chain transfer agent (lactic acid) concentration on bulk viscosity is demonstrated as shown in Table 7.

Table 7

EXAMPLE NO.	% TOTAL SOLIDS	FIRST POLYMER % SOLIDS	SECOND POLYMER % SOLIDS	LACTIC ACID %	% SALT	BV	SV (cps)
98	19	15.2	3.3	0	22.5	760	2.09
99	19	15.2	3.8	0.25	22.5	460	2.86
100	19	15.2	3.8	0.5	22.5	340	2.74

EXAMPLE 101

A suitable vessel equipped with a mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube was charged with 82.15 parts deionized water and 30.8 parts of a 20% aqueous solution of poly(diallyldimethylammonium chloride) (poly(DADMAC)), weight average molecular weight about 289,000. After completion of dissolution, 48.24 parts of a 52.77% aqueous solution of acrylamide and 13.27 parts of an 80% aqueous solution of DEAEA.DMS were added and mixed. To this mixture, 49.5 parts ammonium sulfate, 2.57 parts citric acid, 1.67 parts of 10% lactic acid, and 3.34 parts of 2% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 3.34 parts of 1% V-50. The reaction mixture was raised to 40°C for 2 hours and then raised to and held at 50°C for 4 hours. The combined conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 960 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25°C showing preferable fluidity. The dispersion was dissolved to give a SV of 3.67 cps. This Example demonstrates aqueous dispersions having poly(DADMAC) as the second cationic polymer.

EXAMPLE 102

5 A suitable vessel equipped with an external jacket for heating or cooling, mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube was charged with 262.6 parts deionized water, 47.4 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 41,500, and 92.60 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 205,000. After completion of dissolution, 88.1 parts of a 53.12% aqueous solution of acrylamide and 133.9 parts of a 72.6% aqueous solution of the methyl chloride quaternary salt of diethylaminoethylacrylate (DEAEA.MeCl) were added and mixed. To this mixture, 144 parts ammonium sulfate, 2.644 parts citric acid, and 14.4 parts of 1% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 14.4 parts of 2% V-50. The reaction mixture was raised to and held at 40-45° C for 6 hours. The conversion was greater than 99.9%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 2,200 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25°C. The dispersion was dissolved to give a SV of 3.31 cps. This Example demonstrates an aqueous dispersion having a third cationic polymer.

EXAMPLE 103

20 Polymerization was carried out in the same manner as Example 102, except that the two poly(DMAEM.MeCl) polymers were replaced with a single poly(DMAEM.MeCl) having a weight average molecular weight of about 1,500,000. The bulk viscosity of this dispersion was about 8,000 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25°C showing preferable fluidity. The dispersion was dissolved to give a SV of 2.45 cps.

EXAMPLE 104

30 A suitable vessel equipped with an external jacket for heating, mechanical stirrer, reflux condenser, thermocouple and nitrogen inlet tube was charged with 23.8 parts deionized water and 25.3 parts of a 20% aqueous solution of poly(DADMAC), weight average molecular weight about 289,000. After completion of dissolution, 7.9 parts of a 53.1% aqueous solution of acrylamide and 11.3 parts of a 77.9% aqueous solution of

DEAEA.MeCl were added and mixed. To this mixture, 18 parts ammonium sulfate, 1.08 parts citric acid, 0.37 part of 5% EDTA, and 0.9 part glycerol were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 1.3 parts of 1% V-50 at 40°C. This temperature was held for 2 hours and then was raised to 50°C and maintained at this temperature for 8 hours. The residual acrylamide level was about 209 parts per million (ppm). A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 2,950 cps as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25°C showing preferable fluidity. The dispersion was dissolved to give a SV of 2.47 cps.

EXAMPLES 105-108

Polymerizations were carried out in the same manner as Example 104, except that part of the poly(DADMAC) was replaced with a poly(DADMAC) polymer having a lower weight average molecular weight. The effect on the aqueous dispersion bulk viscosity of including the third polymer is shown in Table 8.

Table 8

	%	FIRST	SECOND	SECOND	THIRD	THIRD			
	TOTAL	POLYMER	POLYMER	POLYMER	POLYMER	POLYMER	%	SV	SV
NO.	SOLIDS	% SOLIDS	% SOLIDS	MW	% SOLIDS	MW	SALT	(cps)	(cps)
104	21.2	14.5	5.06	289,000			20	2,950	2.47
105	21.2	14.5	3.73	289,000	1.89	10,100	20	2,200	2.4
106	21.2	14.5	3.73	289,000	1.89	53,400	20	1,950	2.4
107	21.2	14.5	3.73	289,000	1.89	67,900	20	2,020	2.39
108	21.2	14.5	3.73	289,000	1.89	100,000	20	1,990	2.42

EXAMPLE 109

5 An aqueous dispersion containing 12.5% ammonium sulfate and having a polymer solids of 30%, a bulk viscosity of about 7200 cps and a standard viscosity of about 2.34 cps was prepared in the same manner as in Example 2.

EXAMPLE 110

10 An aqueous dispersion containing 15.5% ammonium sulfate and having a polymer solids level of 28%, a bulk viscosity of about 2640 cps and a standard viscosity of about 2.4 cps was prepared in the same manner as in Example 9.

EXAMPLES 111-133

15 Various amounts of either ammonium sulfate, sodium thiocyanate, or 1,3-benzenedisulfonate (1,3-BDS) were added to the base aqueous dispersions of Example 109, Example 110, Example 103, Example 1, Example 102 and Example 142. The bulk viscosities of the resultant aqueous dispersions were further reduced as shown in Table 9. These Examples demonstrate that the bulk viscosity of aqueous dispersions may be
20 reduced by adding salt to the dispersion, and that the addition of 1,3-BDS may be more effective than ammonium sulfate on a weight basis. Substantially similar results are obtained by polymerizing the monomers in the presence of the salts.

Table 9

Example No.	Base Aqueous Dispersion	BV of Base Aqueous Dispersion	Added Salt	% Total Salt	% Total Solids	BV (cps)
111	Example 109	7200	(NH ₄) ₂ SO ₄	14.21	29.41	2100
112	Example 109	7200	(NH ₄) ₂ SO ₄	15.86	28.84	1,000
113	Example 109	7200	(NH ₄) ₂ SO ₄	17.45	28.3	501
114	Example 109	7200	(NH ₄) ₂ SO ₄	19	27.8	319
115	Example 109	7200	1,3-BDS	13.37	29.7	2200
116	Example 109	7200	1,3-BDS	14.21	29.41	1160
117C	Example 109	7200	1,3-BDS	15	29.12	FL
118	Example 110	2640	NaSCN	16.3	27.7	540
119C	Example 110	2640	NaSCN	17.15	27.45	FL
120C	Example 110	2640	NaSCN	17.96	27.18	FL
121	Example 103	8000	1,3-BDS	19.6	24.51	1660
122	Example 103	8000	1,3-BDS	21.15	24.04	762
123	Example 103	8000	1,3-BDS	22.64	23.58	FL
124	Example 103	8000	(NH ₄) ₂ SO ₄	19.6	24.51	3440
125	Example 103	8000	(NH ₄) ₂ SO ₄	21.15	24.04	1990
126	Example 103	8000	(NH ₄) ₂ SO ₄	22.64	23.58	1300
127	Example 103	8000	(NH ₄) ₂ SO ₄	24.07	23.15	982
128	Example 1	2300	(NH ₄) ₂ SO ₄	19	27.8	501
129	Example 102	2200	(NH ₄) ₂ SO ₄	19.6	24.51	1002
130	Example 102	2200	(NH ₄) ₂ SO ₄	21.15	14.04	441
131	Example 102	2200	(NH ₄) ₂ SO ₄	22.64	23.58	301
132	Example 102	2200	(NH ₄) ₂ SO ₄	24.07	23.15	200
133	Example 142	10,000	(NH ₄) ₂ SO ₄	24.07	23.15	1380

C: Comparative
FL: Formed Layers

EXAMPLE 134

5 About 18 parts of the aqueous dispersion of Example 49 and about 20 parts of the aqueous dispersion of Example 91 were intermixed with stirring. The resultant aqueous dispersion blend was stable and very uniform with a bulk viscosity of about 880 cps, demonstrating that differently charged dispersions may be blended to prepare an aqueous dispersion having an intermediate charge. The aqueous dispersion blend had an overall charge of about 40% and a SV of 2.5 cps.

EXAMPLE 135

10 About 18 parts of a high charge aqueous dispersion prepared as in Example 48 and about 18 parts of a low charge aqueous dispersion prepared as in Example 101 were intermixed with stirring. The resultant aqueous dispersion blend was stable and very uniform with a bulk viscosity of about 2300 cps, demonstrating that differently charged dispersions may be blended to prepare an aqueous dispersion having an intermediate charge. The resultant aqueous dispersion contained four different polymers.

EXAMPLE 136 (Comparative)

20 A polymerization was conducted in the same manner as Example 9, except that the DEAEA.DMS was replaced with an equal weight of DMAEA.MeCl. During the process of polymerization, the contents of the vessel became so viscous that stirring became impossible. The product was obtained as a gel without fluidity. This Example demonstrates that replacement of DMAEA.MeCl with DEAEA.DMS results in an aqueous dispersion having a dramatically lower bulk viscosity.

EXAMPLE 137 (Comparative)

30 A polymerization was conducted in the same manner as Example 50, except that the DEAEA.DMS was replaced with an equal weight of DMAEA.MeCl. During the process of polymerization, the contents of the vessel became so viscous that stirring became impossible. The product was obtained as a gel without fluidity. This Example demonstrates that replacement of DMAEA.MeCl with DEAEA.DMS results in an aqueous dispersion having a dramatically lower bulk viscosity.

35

EXAMPLE 138 (Comparative)

5 A polymerization was conducted in the same manner as Example 91, except that the DEAEA.DMS was replaced with an equal weight of DMAEA.MeCl. During the process of polymerization, the contents of the vessel became so viscous that stirring became impossible. The product was obtained as a gel without fluidity. This Example demonstrates that replacement of DMAEA.MeCl with DEAEA.DMS results in an aqueous dispersion having a dramatically lower bulk viscosity.

EXAMPLE 139 (Comparative)

10 A polymerization was conducted in the same manner as Example 100, except that the DEAEA.DMS was replaced with an equal weight of DMAEA.MeCl. During the process of polymerization, the contents of the vessel became so viscous that stirring became impossible. The product was obtained as a gel without fluidity. This Example demonstrates that replacement of DMAEA.MeCl with DEAEA.DMS results in an aqueous dispersion having a dramatically lower bulk viscosity.

EXAMPLE 140

20 A suitable vessel equipped with a mechanical stirrer, reflux condenser, and nitrogen inlet tube was charged with 20 parts deionized water and 10.51 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 210,000. After completion of dissolution, 6.57 parts of a 53.27% aqueous solution of acrylamide, 14.56 parts of an 80% aqueous solution of DMAEA.MeCl and 4.15 parts of a 80% aqueous solution of DMAEA.BzCl were added and mixed. To this mixture, 10.8 parts ammonium sulfate, 0.4 parts citric acid, and 1.51 parts of 1% EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 1.08 parts of 1% V-50. The reaction mixture was raised to 40°C for 2 hours by placing the vessel in a water bath and then raised to 50° C for 6 hours. The conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of this dispersion was about 2000 cps showing preferable fluidity as measured with a Brookfield Viscometer No. 4 spindle, 30 rpm at 25°C. The dispersion was dissolved to give a SV of 2.2 cps.

EXAMPLES 141-144

Polymerizations were carried out in the same manner as Example 140. The effect of the composition of the first polymer (given in terms of % AMD, % DMAEA.MeCl, and DMAEA.BzCl in monomer feed) and molecular weight of the poly(DMAEM.MeCl) on the aqueous dispersion bulk viscosity is shown in Table 10.

Table 10

	%	%	%	%	FIRST	SECOND	SECOND			
				TOTAL	POLYMER	POLYMER	POLYMER	%	BV	SV
NO.	AMD	DMAEA.MeCl	DMAEA.BzCl	SOLIDS	% SOLIDS	% SOLIDS	MW	SALT	(cps)	(cps)
140	60	25	15	25	18	7	210,000	18	2,000	2.2
141	60	25	15	25	18	7	500,000	18	13,200	2.34
142	60	25	15	25	18	7	1,500,000	18	10,000	2.4
143	60	25	15	25	18	7	800,000	18	11,500	2.2
144	60	29.2	10.8	25	19	6	200,000	18	8,680	2.59

EXAMPLES 145-150 (Comparative)

Polymerizations were carried out in the same manner as Example 140 at different ratios of AMD/DMAEA.MeCl/DMAEA.BzCl/DEAEA.DMS except that the poly(DMAEM.MeCl) was omitted. During the polymerization process, the contents of the vessel became very viscous to the point that stirring became impossible. The resulting polymerization product was obtained as a clear gel, a homogeneous composition without fluidity as shown in Table 11.

Table 11

		%	%	%	%	%	BV
NO.	AMD	DMAEA.MeCl	DMAEA.BzCl	DEAEA.DMS	SOLIDS	SALT	(cps)
145C	50	40	10		14.4	20	Gel
146C	45	40	15		14.4	20	Gel
147C	60	29.2	10.8		18	18	Gel
148C	60	25	15		18	18	Gel
149C	55		5	40	18	18	Gel
150C	55		5	40	25	18	Gel

C: Comparative

EXAMPLES 151-153

An aqueous dispersion having a bulk viscosity of about 3570 cps was prepared in the same manner as Example 13. The dispersion was concentrated by placing about 135 parts into a suitable vessel and heating to 45°C under flowing nitrogen. A total of 26 parts of water was removed in two stages by this dehydration process. The aqueous dispersion remained stable demonstrating that dehydration is effective for achieving high solids, low bulk viscosity aqueous dispersions as shown in Table 12.

Table 12

Example No.	Polymer Solids (%)	Bulk Viscosity (cps)
151 (as polymerized)	28.0	3570
152	31.5	660
153	34.6	3260

EXAMPLE 154

A suitable vessel equipped with a mechanical stirrer, reflux condenser, and a nitrogen inlet tube was charged with 277.75 parts deionized water and 112.0 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 200,000. After completion of dissolution, 89.03 parts of a 53.64% aqueous solution of acrylamide, and 164.93 parts of an 80% solution of DEAEA.DMS were added and mixed. To this mixture, 124.0 parts ammonium sulfate, 9.36 parts citric acid, and 5.02 parts of a 1% solution of EDTA were added and mixed. The pH of the mixture was about 3.3. The contents were heated to 48° C and sparged with nitrogen for 30 minutes, and then polymerization was started by adding 17.92 parts of 1% aqueous solution of V-50. The reaction mixture was maintained at 48° C for 5 hours. About 3.5 hours into the polymerization the aqueous dispersion bulk viscosity began to noticeably increase. The final bulk viscosity of the aqueous dispersion was about 8,000 cps as measured with a Brookfield Viscometer No. 4 spindle, 30 rpm at 25° C.

EXAMPLE 155-156

Duplicate polymerizations were carried out in a similar manner to Example 154 except that an additional amount of ammonium sulfate (4% on total) was added approximately 3 hours after initiation of polymerization. This prevented any substantial increase in bulk viscosity during the polymerization and resulted in a final bulk viscosity that was lower than the bulk viscosity obtained in Example 154 as shown in Table 13.

Table 13

<u>Example No.</u>	<u>Final Bulk Viscosity (#4 spindle, 30 rpm)</u>
155	300 cps
156	500 cps

EXAMPLES 157-172

General Polymerization Procedure: The following components were mixed together in a suitable vessel and the pH was adjusted to about 3.5 with a 28 wt. % solution of ammonium hydroxide.

5	Acrylamide (55.5 wt. %)	5.34 parts
	DEAEA.DMS (80 wt. %)	10.35 parts
	Citric acid	0.58 parts
10	Ammonium sulfate	7.78 parts
	poly(DMAEM.MeCl) (40 wt. %, 200,000 MW)	7.03 parts
	Deionized Water	16.22 parts
	V-50 (1 wt. %)	1.12 parts
	EDTA (1 wt. %)	1.57 parts
15	Methylenebisacrylamide (MBA)	variable
	Lactic acid (chain transfer agent)	variable

Forty parts of the solution were placed into a suitable vessel and the solution was sparged with nitrogen. The vessel was sealed and placed into a 40°C water bath for 2 hours. The temperature was then increased to 50°C and maintained for an additional 3 hours. Results are summarized in Table 14, showing that substantial levels of branching agent and chain transfer agent can be incorporated into aqueous dispersions of water-soluble and water-swelling polymers. The aqueous viscosity values were obtained by dissolving or dispersing the aqueous dispersions in the same general manner as for the standard viscosity values described above, except that the polymer concentration was 0.135 wt. %.

Table 14

Ex. No.	Lactic acid (wt. % on monomer)	MBA (ppm on monomer)	Dispersion bulk viscosity (#4 spindle, 30 rpm)	Aqueous Viscosity
157	0	0	-	3.91
158	0.4	0	-	3.41
159	0.8	0	-	3.04
160	0	0	1100	3.71
161	0	2	1000	3.61
162	0	4	1600	3.66
163	0	6	2500	3.31
164	0	0	2200	3.11
165	0	10	3300	1.90
166	0	15	3300	1.77
167	0	20	8100	1.67
168	0	0	1200	2.81
169	0	30	1800	1.46
170	0	40	3500	1.43
171	0	50	-	1.44
172	0	100	-	1.28

EXAMPLE 173

A aqueous dispersion was prepared as in Example 155. The aqueous dispersion had a bulk viscosity of about 240 cps and an aqueous viscosity (obtained as in Examples 157-172) of 3.55 cps.

EXAMPLE 174

The aqueous dispersion of Example 173 was spray-dried on a commercially available laboratory spray dryer. The chamber of the laboratory spray dryer was 760 millimeters (mm) in diameter with a 860 mm vertical side and a 65 degree conical bottom. Nominal gas flow

through the dryer was about 180 cubic meters per hour. The aqueous dispersion feed was fed at the center of the top of the chamber using a variable speed pump, through a two-fluid nozzle using air for atomization. The outlet gas temperature was 86°C and controlled by varying the inlet gas temperature (169° C) and the feed rate (60 milliliters/minute). To provide an inert atmosphere, the spray-dryer was supplied with nitrogen gas from a cryogenic storage tank. The dried polymer product was discharged through the bottom of the dryer cone to a cyclone where the dry product was removed and collected. Residence time in the dryer was about 14 seconds. The resultant spray-dried polymer particles, which had a volatiles content of 3.4% and a bulk density of about 0.50 grams per cubic centimeter (g/cc), were readily soluble in water and had a SV a 3.49 cps.

EXAMPLE 175

The dissolution rate of the spray-dried polymer of Example 174 was compared to a dry polymer of similar composition obtained by spray-drying a commercial water-in-oil emulsion. Solutions were prepared in a wide mouth quart jar using a 2.5 inch magnetic stirring bar. The stirring rate was adjusted so that a deep vortex was obtained in the water. The dry polymer was added slowly over a period of 5 minutes at the edge of the vortex to avoid clumping. The spray-dried polymer of Example 174 wet more readily and completely dissolved over a period of 30-40 minutes, giving a clear solution. In contrast, the dry polymer obtained by spray-drying an inverse emulsion did not wet as rapidly and was not completely dissolved after two hours. This Example demonstrates that a dry polymer obtained by spray-drying an aqueous dispersion of the instant invention dissolved faster than a dry polymer obtained by spray-drying a corresponding water-in-oil emulsion.

EXAMPLE 176C

The procedure of U.S. Patent No. 5,403,883 Example 1 was followed. A dispersion having a bulk viscosity of about 10,600 cps (#4 spindle, 30 rpm) was obtained.

EXAMPLE 177

The procedure of U.S. Patent No. 5,403,883 Example 1 was followed, except that the 2-trimethylammoniummethyl acrylate chloride was replaced by an equal weight of

DEAEA.MeCl. The resulting aqueous dispersion had a bulk viscosity of about 6,900 cps (#4 spindle, 30 rpm), demonstrating improved bulk viscosity as compared to Example 176C.

EXAMPLE 178

5 A suitable vessel equipped with a mechanical stirrer, reflux condenser, and a nitrogen inlet tube was charged with 22.94 parts deionized water and 10.5 parts of a 40% aqueous solution of poly(DMAEM.MeCl), weight average molecular weight about 245,000. After completion of dissolution, 6.47 parts of a 54.20% aqueous solution of acrylamide, and 7.49
10 parts of the propyl chloride quaternary salt of dimethylaminoethyl acrylate were added and mixed. To this mixture, 10.8 parts ammonium sulfate, 0.7 parts citric acid, and 0.76 parts of a 2% solution of EDTA were added and mixed. The pH of the mixture was about 3.3. The vessel was sealed and sparged with nitrogen for 30 minutes, and then polymerization was started by addition of 0.54g of 2% aqueous solution of V-50. The reaction mixture was
15 heated to 40°C for 2 hours and then raised to 50° C and held for an additional 4 hours. The conversion was greater than 99%. A stable fluid aqueous dispersion was obtained. The bulk viscosity of the aqueous dispersion was about 1300 cps showing preferable fluidity as measured with a Brookfield Viscometer, No. 4 spindle, 30 rpm at 25° C. The aqueous dispersion was dissolved to give a SV of 2.1 cps. This Example demonstrates that, despite
20 Comparative Example 1 of EP 0 525 751 A1, an aqueous dispersion may be formed when the first polymer contains recurring units of the propyl chloride quaternary salt of dimethylaminoethylacrylate.

EXAMPLE 179

25 An aqueous dispersion was prepared in a similar manner to Example 40 except that the first polymer composition was AMD/DEAEA.DMS/DMAEA.MeCl (60/30/10 mole). The aqueous dispersion had a bulk viscosity of about 3,600 cps (No. 4 spindle, 30 rpm at 25° C) and a SV of 2.64 cps.

EXAMPLE 180

30 An aqueous dispersion was prepared in a similar manner to Example 40 except that the first polymer composition was AMD/DEAEA.DMS/DMAEA.MeCl (60/25/15 mole). The aqueous dispersion had a bulk viscosity of about 1,000 cps (No. 4 spindle, 30 rpm at 25°
35 C) and a SV of 2.87 cps.

EXAMPLES 181-261

5 The performance of aqueous dispersions of the instant invention was determined
by measuring free drainage rate and cake solids from dewatered sludge as follows: Two
hundred grams of sewage sludge from a municipal waste treatment plant were weighed into
each of a series of jars. Solutions of the aqueous dispersions and of W/O, a commercial
water-in-oil emulsion control (60/40 mole % AMD/DMAEA.MeCl), were prepared so that the
concentration of the polymer was about 0.2%. Various doses of the polymer solutions were
intermixed with the sludge samples and agitated at 500 rpm for 10 seconds (500 rpm/10
10 seconds) or at 1000 rpm for 5 seconds (1000 rpm/5 seconds) with an overhead mixer. The
resultant aqueous mixture of flocculated sludge was dewatered by pouring it into a Buchner
funnel containing a 35 mesh stainless steel screen; the free drainage was determined by
measuring the milliliters of filtrate collected in 10 seconds. Cake solids were determined
by drying the pressed sludge at 105°C. The results are shown in Table 15, with each
15 polymer identified by previous Example No., free drainage in units of milliliters/10 seconds,
mixing in rpm/seconds, dosage in units of pounds of polymer per ton of dry sludge, and
cake solids as a weight percent of dry solids in wet cake. The notation "N/A" in the Table
means that an accurate cake solids value could not be obtained. These Examples show that
the performance of the aqueous dispersions of the instant invention is substantially
20 equivalent or superior to a comparable commercial product.

Table 15

No.	Polymer	Mixing	Dosage	Free Drainage	Cake Solids (%)
181	102	500/10	24.4	137	17.3
182	102	500/10	26.7	140	16.9
183	102	500/10	28.9	128	17.1
184	103	500/10	20	138	15.8
185	103	500/10	22.2	155	16.5
186	103	500/10	24.4	158	16.5
187	103	500/10	26.7	162	15.7
188C	W/O	500/10	24.4	112	15.0
189C	W/O	500/10	26.7	122	15.6
190C	W/O	500/10	28.9	114	15.2
191	102	1000/5	20.2	142	15.5
192	102	1000/5	22.2	145	15.8
193	102	1000/5	26.7	140	15.3
194	103	1000/5	24.4	130	15.7
195	103	1000/5	26.7	138	15.8
196	103	1000/5	28.9	145	15.2
197C	W/O	1000/5	22.2	112	16.0
198C	W/O	1000/5	24.4	120	16.2
199C	W/O	1000/5	26.7	110	15.7
200	9	500/10	23	144	16.6
201	9	500/10	27.2	160	17.0
202	9	500/10	31.4	140	17.1
203	179	500/10	23	144	17.0
204	179	500/10	27.2	153	17.6
205	179	500/10	31.4	152	17.4
206	180	500/10	23	100	16.9
207	180	500/10	27.2	130	16.8
208	180	500/10	31.4	125	17.1

	209C	W/O	500/10	23	99	14.9
	210C	W/O	500/10	27.2	92	15.2
5	211	9	1000/5	25.1	96	17.6
	212	9	1000/5	29.3	97	18.0
	213	9	1000/5	31.4	93	17.9
	214	179	1000/5	29.3	107	17.7
10	215	179	1000/5	31.4	92	18.4
	216	179	1000/5	35.6	104	18.7
	217	180	1000/5	25.1	84	16.9
	218	180	1000/5	29.3	92	17.9
15	219	180	1000/5	31.4	136	17.1
	220	180	1000/5	35.6	104	17.1
	221C	W/O	1000/5	25.1	110	16.1
	222C	W/O	1000/5	29.3	112	16.5
20	223C	W/O	1000/5	31.4	108	16.8
	224	44	500/10	22.1	140	17.5
	225	44	500/10	24.5	138	17.0
	226	44	500/10	27	139	17.4
25	227	44	1000/5	22.1	120	19.0
	228	44	1000/5	25.8	117	19.3
	229	44	1000/5	29.4	104	19.5
	230C	W/O	500/10	18.4	108	NA
30	231C	W/O	500/10	22.1	110	NA
	232C	W/O	500/10	25.8	66	NA
	233C	W/O	1000/5	22.1	128	17.9
35	234C	W/O	1000/5	25.8	102	17.6
	235	61	500/10	16.9	130	17.2
	236	61	500/10	18.6	140	18.0
	237	61	500/10	21.9	130	17.3
40	238	67	500/10	15.2	80	16.8

	239	67	500/10	16.9	105	17.8
	240	67	500/10	18.6	126	18.2
5	241C	W/O	500/10	15.2	116	16.2
	242C	W/O	500/10	16.9	116	15.6
	243C	W/O	500/10	18.8	82	15.4
	244	140	500/10	26.5	138	18.0
	245	140	500/10	29.4	140	18.5
10	246	140	500/10	32.4	130	18.2
	247	140	1000/5	29.2	118	17.8
	248	140	1000/5	32.4	129	18.4
	249	140	1000/5	35.7	137	19.0
15						
	250	142	500/10	26.5	120	16.9
	251	142	500/10	29.4	142	17.2
	252	142	500/10	32.4	127	17.1
20	253	142	1000/5	25.9	120	17.3
	254	142	1000/5	29.2	140	17.8
	255	142	1000/5	32.4	138	18.3
	256C	W/O	500/10	14.7	76	14.0
25	257C	W/O	500/10	17.6	114	14.8
	258C	W/O	500/10	20.6	105	14.8
	259C	W/O	1000/5	22.7	104	16.8
	260C	W/O	1000/5	25.9	134	16.3
30	261C	W/O	1000/5	29.2	113	16.7

C: Comparative

W/O: Commercially available water-in-oil emulsion copolymer of acrylamide and DMAEA.MeCl (60/40 mole %)

EXAMPLES 262-263

5 The performance of the aqueous dispersions of Examples 118 and 121 is determined by measuring free drainage rate and cake solids from dewatered sludge by following the procedure of Examples 181-261. Similar results are obtained.

EXAMPLE 264

10 A solution of the spray-dried polymer of Example 174 is prepared so that the concentration of the polymer is about 0.2%. The performance is determined by measuring free drainage rate and cake solids from dewatered sludge by following the procedure of Examples 181-261. Similar results are obtained.

EXAMPLES 265-277

15 Solutions of the aqueous dispersions and spray-dried polymers of Examples 9, 44, 61, 67, 102, 103, 118, 121, 140, 142, 174, 179, and 180 are prepared so that the concentration of the polymer is about 0.2%. The performance is determined by measuring free drainage rate by following the procedure of Examples 181-261, except that a 1% suspension of paper solids is dewatered instead of sewage sludge. Similar results are obtained.

EXAMPLES 278-293

25 Aqueous admixtures are prepared by intermixing the aqueous dispersions of Examples 157-172 with water so that the concentration of the polymer is about 0.2%. The performance is determined by measuring free drainage rate by following the procedure of Examples 181-261, except that a 1% suspension of paper solids is dewatered instead of sewage sludge. Similar results are obtained.

30

We Claim:

1. A composition comprising an aqueous dispersion comprised of:

(a) a first cationic water-soluble or water-swellaable polymer; and

(b) at least one second water-soluble polymer different from said first polymer; and


(c) a kosmotropic salt; and

(d) a chaotropic salt or an anionic organic salt,

wherein the amounts of said (b), (c) and (d) are such that a homogeneous composition is obtained in the absence of said (b).

2. A composition comprising an aqueous dispersion comprised of:

(a) a discontinuous phase containing polymer that is comprised predominately of a first cationic water-soluble or water-swellaable polymer having at least one recurring unit of the formula (I),




wherein R₁ is H or CH₃, A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R₂ is a methyl, ethyl, or propyl group, R₃ is a methyl, ethyl, or propyl group, R₄ is a methyl, ethyl, or propyl group, X is a counterion, and R₂, R₃ and R₄ together contain a total of at least 4 carbon atoms; and

(b) at least one second water-soluble polymer different from said first polymer.

3. A composition comprising an aqueous dispersion comprised of:

(a) a discontinuous phase containing polymer that is comprised predominately of a first cationic water-soluble or water-swellaible polymer having at least one recurring unit of the formula (I),



wherein R₁ is H or CH₃, A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R₂ is a methyl, ethyl, or propyl group, R₃ is a methyl, ethyl, or propyl group, R₄ is an alkyl or substituted alkyl group having from 1 to 10 carbons, or an aryl or substituted aryl group having from 6 to 10 carbons, X is a counterion, and R₂, R₃, and R₄ together contain a total of at least 4 carbon atoms; and

(b) at least one second water-soluble polymer different from said first polymer,

wherein a homogeneous composition is obtained in the absence of said (b).

4. A composition as claimed in Claim 2 or 3 which is further comprised of an inorganic salt selected from the group consisting of chlorides, sulfates, phosphates, hydrogenphosphates and mixtures thereof.

5. A composition as claimed in Claim 2, 3 or 4 wherein said first polymer is further comprised of hydrophobic recurring units.

6. A process which comprises polymerizing vinyl-addition monomers to form an aqueous dispersion comprised of a first cationic water-soluble or water-swellable polymer, wherein said polymerizing is carried out in the presence of an aqueous composition comprised of


(a) at least one second water-soluble polymer different from said first polymer; and

(b) a kosmotropic salt; and

(c) a chaotropic salt or anionic organic salt,

wherein the amounts of said (a), (b) and (c) are such that a homogeneous composition is obtained if said polymerizing is carried out in the absence of said (a).


7. A process which comprises polymerizing vinyl-addition monomers comprised of at least one monomer of the formula (II) to form an aqueous dispersion comprised of a first cationic water-soluble or water-swellable polymer,



wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is a methyl, ethyl, or propyl group, X is a counterion, and R_2 , R_3 and R_4 together contain a total of at least 4 carbon atoms; and

wherein said polymerizing is carried out in the presence of an aqueous composition comprised of at least one second water-soluble polymer different from said first polymer.

8. A process which comprises polymerizing vinyl-addition monomers comprised of at least one monomer of the formula (II) to form an aqueous dispersion comprised of a first cationic water-soluble or water-swellaable polymer,



wherein R₁ is H or CH₃, A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R₂ is a methyl, ethyl, or propyl group, R₃ is a methyl, ethyl, or propyl group, R₄ is an alkyl or substituted alkyl group having from 1 to 10 carbons, or an aryl or substituted aryl group having from 6 to 10 carbons, X is a counterion, and R₂, R₃ and R₄ together contain a total of at least 4 carbon atoms; and

wherein said polymerizing is carried out in the presence of an aqueous composition comprised of an amount of at least one second water-soluble polymer different from said first polymer; and

wherein said amount of said second polymer is such that a homogeneous composition is obtained if said polymerizing is carried out in the absence of said second polymer.

9. A process as claimed in Claim 7 or 8 wherein said aqueous composition is further comprised of an inorganic salt selected from the group consisting of chlorides, sulfates, phosphates, and hydrogenphosphates.

10. A process as claimed in Claim 7, 8 or 9 wherein said vinyl-addition monomers are further comprised of a hydrophobic monomer.

11. A method comprising (a) intermixing an aqueous dispersion of polymers, or aqueous admixture thereof, in an amount effective for dewatering, with a suspension of dispersed solids, and (b) dewatering said suspension of dispersed solids, said aqueous dispersion being comprised of

5 (i) a first cationic water-soluble or water-swellaable polymer; and

(ii) at least one second water-soluble polymer different from said first polymer; and

10 (iii) a kosmotropic salt; and

(iv) a chaotropic salt or anionic organic salt,

15 wherein the amounts of said (ii), (iii) and (iv) are such that a homogeneous composition is obtained in the absence of said (ii).

12. A method comprising

20 (a) intermixing an aqueous dispersion of polymers, or aqueous admixture thereof, in an amount effective for clarification, with oil-containing water to produce clarified water, and (b) separating said clarified water from said oil, said aqueous dispersion being comprised of

(i) a first cationic water-soluble or water-swellaable polymer; and

25 (ii) at least one second water-soluble polymer different from said first polymer; and


(iii) a kosmotropic salt; and

30 (iv) a chaotropic or anionic organic salt,

wherein the amounts of said (ii), (iii), and (iv) are such that a homogeneous composition is obtained in the absence of said (ii).

13. A method comprising (a) intermixing an aqueous dispersion of polymers, or aqueous admixture thereof, in an amount effective for dewatering, with a suspension of dispersed solids, and (b) dewatering said suspension of dispersed solids, said aqueous dispersion being comprised of

(i) a discontinuous phase containing polymer that is comprised predominately of a first cationic water-soluble or water-swellaable polymer having at least one recurring unit of the formula (I),



wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is a methyl, ethyl, or propyl group, X is a counterion, and R_2 , R_3 and R_4 together contain a total of at least 4 carbon atoms; and


(ii) at least one second water-soluble polymer different from said first polymer.

14. A method comprising

(a) intermixing an aqueous dispersion of polymers, or aqueous admixture thereof, in an amount effective for clarification, with oil-containing water to produce clarified water, and (b) separating said clarified water from said oil, said aqueous dispersion being comprised of

(i) a discontinuous phase containing polymer that is comprised predominately of a first cationic water-soluble or water-swellaable polymer having at least one recurring unit of the formula (I),

(I)



5

10

wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is a methyl, ethyl, or propyl group. X is a counterion, and R_2 , R_3 and R_4 together contain a total of at least 4 carbon atoms; and

15

(ii) at least one second water-soluble polymer different from said first polymer.


20

15. A method comprising (a) intermixing an aqueous dispersion of polymers, or aqueous admixture thereof, in an amount effective for dewatering, with a suspension of dispersed solids, and (b) dewatering said suspension of dispersed solids, said aqueous dispersion being comprised of

25

(i) a discontinuous phase containing polymer that is comprised predominately of a first cationic water-soluble or water-swellaable polymer having at least one recurring unit of the formula (I),

(I)



30

35

wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl,

ethyl, or propyl group, R_4 is an alkyl or substituted alkyl group having from 1 to 10 carbons, or an aryl or substituted aryl group having from 6 to 10 carbons. X is a counterion, and R_2 , R_3 and R_4 together contain a total of at least 4 carbon atoms; and


(ii) at least one second water-soluble polymer different from said first polymer,

wherein a homogeneous composition is obtained in the absence of said (ii).

16. A method comprising

(a) intermixing an aqueous dispersion of polymers, or aqueous admixture thereof, in an amount effective for clarification, with oil-containing water to produce clarified water, and (b) separating said clarified water from said oil, said aqueous dispersion being comprised of

(i) a discontinuous phase containing polymer that is comprised predominately of a first cationic water-soluble or water-swellaable polymer having at least one recurring unit of the formula (I),



wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is an alkyl or substituted alkyl group having from 1 to 10 carbons, or an aryl or substituted aryl group having from 6 to 10 carbons, X is a counterion, and R_2 , R_3 and R_4 together contain a total of at least 4 carbon atoms; and

(ii) at least one second water-soluble polymer different from said first polymer,

wherein a homogeneous composition is obtained in the absence of said (ii).

17. A method as claimed in Claim 13, 14, 15 or 16 wherein said aqueous dispersion is further comprised of an inorganic salt selected from the group consisting of chlorides, sulfates, phosphates, hydrogenphosphates and mixtures thereof.

5 18. A method as claimed in Claim 13, 14, 15, 16 or 17 wherein said first polymer is further comprised of hydrophobic recurring units.

19. A method as claimed in Claim 11, 13 or 15 wherein said suspension comprises paper solids, mineral solids, food solids, or a biologically treated suspension.

10 20. A process for producing substantially dry water-soluble or water-swellaable vinyl-addition polymer particles comprising (a) spray-drying a vinyl-addition polymer-containing aqueous dispersion into a gas stream with a residence time of about 8 to about 120 seconds and at an outlet temperature of about 70° C to about 100° C and (b) collecting
15 resultant polymer particles.

21. A composition comprising substantially dry water-soluble or water-swellaable polymer particles comprised of

20 (a) a first cationic water-soluble or water-swellaable polymer; and

(b) at least one second water-soluble polymer different from said first polymer; and

(c) a kosmotropic salt; and


25 (d) a chaotropic salt or an anionic organic salt,

wherein about 90% or more of said polymer particles each individually contains both said (a) and said (b), said particles having a bulk density of about 0.4 grams per cubic
30 centimeter to about 1.0 grams per cubic centimeter.

22. A composition comprising substantially dry water-soluble or water-swellaable polymer particles comprised of

(a) a first cationic water-soluble or water-swellaable polymer having at least one recurring unit of the formula (I),

(I)



wherein R_1 is H or CH_3 , A is O or NH, B is an alkylene or branched alkylene or oxyalkylene group having from 1 to 5 carbons, R_2 is a methyl, ethyl, or propyl group, R_3 is a methyl, ethyl, or propyl group, R_4 is an alkyl or substituted alkyl group having from 1 to 10 carbons, or an aryl or substituted aryl group having from 6 to 10 carbons, X is a counterion, and R_2 , R_3 and R_4 together contain a total of at least 4 carbon atoms; and

(b) at least one second water-soluble polymer different from said first polymer,

wherein about 90% or more of said polymer particles each individually contains both said (a) and said (b), said particles having a bulk density of about 0.4 grams per cubic centimeter to about 1.0 grams per cubic centimeter.

23. A method comprising (a) intermixing the composition of Claim 21 or 22 with water to form an aqueous polymer admixture, (b) intermixing said aqueous polymer admixture, in an amount effective for dewatering, with a suspension of dispersed solids, and (c) dewatering said suspension of dispersed solids.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 97/16647

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C02F1/56 C08F220/34

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C02F C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 262 945 A (ALLIED COLLOIDS LTD) 6 April 1988 cited in the application see claim 1 ----	1-8
A	GB 1 498 136 A (HERCULES INC) 18 January 1978 see page 2, line 125 - page 3, line 16 ----	1
A	US 4 699 951 A (ALLENSON STEPHAN J ET AL) 13 October 1987 cited in the application see column 4, line 22-44 ----- -/-	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

12 January 1998

Date of mailing of the international search report

27/01/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Meulemans, R

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 97/16647

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 95 33697 A (CDM AB ;ALLIED COLLOIDS LTD (GB); SORENSEN JENS (SE); FIELD JOHN R) 14 December 1995 cited in the application see claim 1 ----	1
A	US 5 330 656 A (HASSICK DENIS E) 19 July 1994 see the whole document ----	1
A	EP 0 525 751 A (HYMO CORP) 3 February 1993 cited in the application see the whole document -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PCT/US 97/16647

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0262945 A	06-04-88	CA 1329283 A DE 3788696 D DE 3788696 T ES 2061508 T JP 63101443 A US 4835206 A	03-05-94 17-02-94 28-04-94 16-12-94 06-05-88 30-05-89
GB 1498136 A	18-01-78	NONE	
US 4699951 A	13-10-87	US 4588508 A	13-05-86
WO 9533697 A	14-12-95	AU 2677795 A EP 0764140 A ZA 9504744 A	04-01-96 26-03-97 10-06-96
US 5330656 A	19-07-94	NONE	
EP 0525751 A	03-02-93	JP 5032722 A AU 657556 B AU 2059892 A CA 2074758 A DE 69220546 D DE 69220546 T US 5587415 A	09-02-93 16-03-95 04-02-93 31-01-93 31-07-97 11-12-97 24-12-96

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant:

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☒ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.